January 2007

Materials in particulate form for tissue engineering. 1. Basic concepts

Gabriela Silva
University of Minho

Paul Ducheyne
University of Pennsylvania, ducheyne@seas.upenn.edu

R. L. Reis
University of Minho

Follow this and additional works at: https://repository.upenn.edu/be_papers

Recommended Citation

Silva, G., Ducheyne, P., & Reis, R. L. (2007). Materials in particulate form for tissue engineering. 1. Basic concepts. Retrieved from https://repository.upenn.edu/be_papers/120

Postprint version. Published in *Journal of Tissue Engineering and Regenerative Medicine*, Volume 1, Issue 1, January 2007, pages 4-24.

Publisher URL: <http://dx.doi.org/10.1002/term.2>

This paper is posted at ScholarlyCommons. https://repository.upenn.edu/be_papers/120
For more information, please contact repository@pobox.upenn.edu.

Materials in particulate form for tissue engineering. 1. Basic concepts

Abstract

For biomedical applications, materials small in size are growing in importance. In an era where 'nano' is the new trend, micro- and nano-materials are in the forefront of developments. Materials in the particulate form aim to designate systems with a reduced size, such as micro- and nanoparticles. These systems can be produced starting from a diversity of materials, of which polymers are the most used. Similarly, a multitude of methods are to produce particulate systems, and both materials and methods are critically reviewed here. Among the varied applications that materials in the particulate form can have, drug delivery systems are probably the most prominent, as these have been in the forefront of interest for biomedical applications. The basic concepts pertaining to drug delivery are summarized, and the role of polymers as drug delivery systems conclude this review.

Keywords

microparticles, nanoparticles, drug delivery, tissue engineering, polymers, ceramics, natural origin

Comments

Postprint version. Published in *Journal of Tissue Engineering and Regenerative Medicine*, Volume 1, Issue 1, January 2007, pages 4-24.

Publisher URL: <http://dx.doi.org/10.1002/term.2>

Materials in particulate form for tissue engineering.

1. Basic concepts

G. A. Silva^{1,2*}, P. Ducheyne³ and R. L. Reis^{1,2}

¹3Bs Research Group – Biomaterials, Biodegradables, Biomimetics, University of Minho, Campus de Gualtar, 4710-057 Braga, Portugal

²Department of Polymer Engineering, University of Minho, Campus de Azurém, 4800-058 Guimarães, Portugal

³Center for Bioactive Materials and Tissue Engineering, University of Pennsylvania, Philadelphia, PA 19104, USA

Abstract

For biomedical applications, materials small in size are growing in importance. In an era where 'nano' is the new trend, micro- and nano-materials are in the forefront of developments. Materials in the particulate form aim to designate systems with a reduced size, such as micro- and nanoparticles. These systems can be produced starting from a diversity of materials, of which polymers are the most used. Similarly, a multitude of methods are to produce particulate systems, and both materials and methods are critically reviewed here. Among the varied applications that materials in the particulate form can have, drug delivery systems are probably the most prominent, as these have been in the forefront of interest for biomedical applications. The basic concepts pertaining to drug delivery are summarized, and the role of polymers as drug delivery systems conclude this review. Copyright © 2007 John Wiley & Sons, Ltd.

Received 13 December 2006; Accepted 20 December 2006

Keywords microparticles; nanoparticles; drug delivery; tissue engineering; polymers; ceramics; natural origin

Contents

1. Definition
2. Classification of materials in particulate form
3. Overview of synthesis methods
4. Materials used in the synthesis of materials in particulate form
5. Applications
6. Conclusions
- References

1. Definition

The key feature of particulate materials systems being their reduced size, the question regarding the threshold size for considering a system to be a particulate one is of value. Across the literature, many authors differ regarding this question. Herein, micron (μm)-sized systems in the

range 1–1000 μm will be considered first. Nano-sized particle systems, within this context, are those for which the sizes are below 1 μm (Kreuter, 1991), and they will be described next.

2. Classification of materials in particulate form

2.1. Microparticles

Microparticles consist of particles in a size range 1–1000 μm (Couvreur and Puisieux, 1993). These include microcapsules, vesicular systems in which a cavity is surrounded by a unique polymeric membrane, and microspheres, which are matrix-filled systems (Couvreur and Puisieux, 1993). Polymer microspheres have attracted attention as carrier matrices in a wide variety of medical and biological applications, such as affinity chromatography, immobilization, immunoassay, nuclear imaging and cell culture (Tuncel *et al.*, 1996; Kamyshny and Magdassi, 2000; Shinkai, 2002). Additionally, the incorporation of bioactive agents into small polymeric

*Correspondence to: G. A. Silva, Department of Polymer Engineering, University of Minho, Campus de Azurém, 4800-058 Guimarães, Portugal. E-mail: gsilva@dep.uminho.pt

particles was recognized years ago by the pharmaceutical industry as a viable means of improving drug delivery (Bissery *et al.*, 1984; Bezemer *et al.*, 2000a, 2000b; Pillai *et al.*, 2001). This use arose because conventional dosage forms, such as oral delivery and injection, were not able to control the rate of delivery or the target area of the bioactive agent and were often associated with an immediate or rapid release (Tao and Desai, 2003).

The main advantages of microparticles is that they may be administered by injection or intranasally as a dry powder, so that a surgical procedure is not required (Baldwin and Saltzman, 1998; Eliaz and Kost, 2000; Tinsley-Brown *et al.*, 2000), and that they may contain a greater amount of biologically active molecules per unit volume (Langer, 1991; Grassi *et al.*, 2001; Janes *et al.*, 2001a). Various parameters, including particle size and distribution, porosity, pore structure and surface area, are considered to describe the overall performance of polymer microparticles in biomedical applications (Tuncel *et al.*, 1996; Allemann *et al.*, 1998; Yang and Alexandridis, 2000). Additionally, the use of microparticles composed of biodegradable polymers eliminates the need for device removal after release of the agent (Baldwin and Saltzman, 1998). Based on these features, microparticles have been the subject of numerous studies with the intent to overcome a number of issues related to the therapeutics of biologically active molecules.

In summary, microparticles have the following properties that render them attractive:

- *Size*: small size allows them to be inserted in the target area in a non-invasive manner, thus increasing effectiveness.
- *Size distribution*: microparticles ranging from a few to a few hundred μm can be selected according to a specific application.
- *Porosity and pore structure*: the presence of pores allows the tailoring of the release profile.
- *Surface area*: large surface area and a capacity for loading the bioactive agent at a high fraction of the total weight of the particle.

However, for some applications, particles with an even smaller size – nanoparticles – can be preferable to microparticles.

2.2. Nanoparticles

Nanoparticles, being submicron systems, have the advantage of an even larger surface area compared with microparticles, because the total surface area is inversely proportional to the third power of the diameter (Berton *et al.*, 1999; Kawaguchi, 2000). In these systems the bioactive agent can be dissolved, entrapped, encapsulated, adsorbed, immobilized or attached to the matrix (Orive *et al.*, 2004) and, depending upon the method of preparation, nanoparticles, nanospheres or nanocapsules can be obtained (Couvreur and Puisieux, 1993; Soppimath *et al.*, 2001). Nanocapsules are vesicular

systems in which the bioactive agent is confined to a cavity surrounded by a unique polymer membrane, while nanospheres are matrix systems in which the bioactive agent is physically and uniformly dispersed (Soppimath *et al.*, 2001). Nanospheres and nanocapsules are the morphological equivalents of microspheres and microcapsules, respectively (Allemann *et al.*, 1998).

Nanoparticles can be injected and, as a result, can circulate in the blood stream (Madan *et al.*, 1997). However, in some cases, nanoparticles are phagocytosed by macrophages (Lee *et al.*, 2001), and this can lead to an adverse immunological response. However, such reaction may be desirable in applications such as vaccination therapies, and when enhanced uptake of exogenous compounds, such as anti-human immunodeficiency virus (HIV) drugs (Lee *et al.*, 2001), is sought. Nanoparticle polymeric carriers, when their size is less than 100 nm, have a high potential for being accumulated in tumour sites, according to the enhanced permeation and retention (EPR) effect (Nishikawa *et al.*, 1996; Yasugi *et al.*, 1999). Hydrophilic modification, particularly by introducing poly(ethylene)glycol (PEG) by physical coating or covalent linking – a process known as pegylation – to the surface, prolongs the half-life of the carriers (Kumar, 2000; Seal *et al.*, 2001; Diwan and Park, 2003) during circulation in blood by reducing opsonization and thus minimizing carrier clearance in organs such as liver, spleen, lung and bone marrow (Gref *et al.*, 1994; Peracchia *et al.*, 1997). This long-circulating stealth characteristic of the carrier produces the EPR effect, which is valuable in passive cancer targeting (Berthold *et al.*, 1998; Maeda *et al.*, 2000).

Nanoparticles hold great potential for the treatment of tumours. An example is related to the ability of those materials to include within their matrix magnetic particles and by directing nanoparticles to the target (e.g. tumour cells) through magnetic fields created around the tumour. This brings great advantages, such as a reduction of the dosage and side-effects, as well as a rise in the therapeutic effect, together with controlled and, most importantly, direct targeting of the tumour site (Brigger *et al.*, 2002).

Nanoparticles offer other specific advantages over liposomes, because they increase the stability of bioactive agents/proteins and possess a better set of controlled release properties (Jain, 1994; Hrkach *et al.*, 1997; Gaspar *et al.*, 1998; Berton *et al.*, 1999; Kumar, 2000; Soppimath *et al.*, 2001).

To summarize, nanoparticles possess the following advantages:

- *Stability*: increased stability over liposomes and promotion of increased stability of entrapped bioactive molecules.
- *Surface area*: higher surface area, even when compared with microparticles.
- *Size*: depending on their size, they can be phagocytosed or can circulate in the blood long enough to promote the therapeutic effect.

- *Stealth effect*: controlled by size and modification by coating with polymers such as PEG.
- *Delivery to target site*: easily delivered by injection, without the need of invasive procedures.

3. Overview of synthesis methods

There are several methods for the production of micro- and nanoparticles, but the most widely used techniques are methods based in emulsions, such as suspension polymerization, solvent evaporation and, to a smaller extent, organic phase separation (coacervation) and spray-drying methods, as reviewed/described in detail in the literature (Kreuter, 1991; Gref *et al.*, 1994; Tuncel *et al.*, 1996; Madan *et al.*, 1997; O'Donnell and McGinity, 1997; Lin and Yu, 2001; Soppimath *et al.*, 2001).

In suspension polymerization, the monomer phase is broken into droplets (a few μm in diameter) within a dispersion medium (usually an aqueous phase) and stabilized by a surfactant dissolved in the medium (Piskin *et al.*, 1993). These monomer droplets containing a monomer phase soluble initiator are then individually polymerized by applying a temperature/agitation programme (Piskin *et al.*, 1993). In the emulsion/solvent evaporation method, the polymer is solubilized/dispersed in an organic solvent (e.g. methylene chloride, chloroform) and the resultant solution is then emulsified with an aqueous phase (Soppimath *et al.*, 2001; Perez *et al.*, 2002). The formation of the particles is achieved by hardening resulting from the evaporation of the organic solvent. Stirring speed is usually the parameter controlling the size of the particles. This method is easy to implement and yields very good results with a variety of raw materials.

Most of the methods for the production of particle-based systems are actually based on the creation of emulsions between organic and aqueous phases, and suffer one common drawback – the need for organic solvents (e.g. methylene chloride, chloroform, acetonitrile, tetrahydrofuran) in at least one of the production steps (Ghaderi *et al.*, 1999; Kim and Park, 1999; Sendil *et al.*, 1999; Birnbaum *et al.*, 2000). The residual content of the organic solvent in the microparticles after preparation has to be removed in time-consuming drying steps (Nykamp *et al.*, 2002), and in many cases the presence of an organic solvent can lead to loss of the activity of the agent to be loaded into the system. Currently, methods that obviate the use of organic solvents are in demand, and this aspect is particularly critical when there is a risk of hindering the activity of the biological agent. An interesting new approach in efforts to address this particular issue is that described by Nykamp *et al.* (2002), who used a jet-milling technique to produce polylactic acid (PLA) and polylactic/glycolic acid (PLGA) microparticles with different ratios of the two polymers. Conceivably, this method could also be used for other polymers. However, the first step of this process involves melting the starting

material, which obviously has to be taken into account when aiming to use the developed systems for delivery of bioactive agents. Similarly, Lin *et al.* (1999) have used a solvent-free method to produce polycaprolactone (PCL) microparticles, by dispersing polyethylene glycol (PEG) in the PCL phase. Although the melting temperature of PCL is low (close to 60°C), this temperature might still be deleterious for the activity of bioactive molecules.

One has to be cautious in choosing the method of production, and weigh carefully between the risks of using an organic solvent or using high-temperature conditions, two major parameters influencing the biological activity of an agent.

Although micro- and nanoparticles can be produced using a vast array of possible techniques, a number of variables that affect the product obtained have to be taken into account when choosing a material and method. These include (Bissery *et al.*, 1984; Ronneberger *et al.*, 1997; Bezemer *et al.*, 2000a):

- Type and amount of material used.
- Degradation rate of the polymer.
- Type and payload of bioactive agent being incorporated (in case of drug delivery applications).
- Organic solvent being volatilized.
- Type and amount of surfactant dissolved in the aqueous phase.
- Temperature.
- Pressure during solvent evaporation.
- Ratio of the volume of organic solvent:volume of aqueous phase.

By 'playing' with these parameters, researchers have been able to use a wide array of materials and methods for a number of applications.

4. Materials used in the synthesis of materials in particulate form

The polymeric class of materials has been regarded as the primary choice for applications in which small-sized particles are needed, since many polymers can be formed into microparticles and nanoparticles for delivery and other applications. These may be non-degradable or degradable polymers, from synthetic or natural origin, or even blends (synthetic–synthetic, synthetic–natural or natural–natural). Nevertheless, polymers are not the only materials used for producing materials in particulate form; across the literature there is a wide array of materials used for the synthesis of particle-based materials, including ceramics and metals. This review deals primarily with polymers and to some extent ceramics. Some examples of polymer–ceramic composites will also be described.

Table 1 summarizes the most frequently used materials for the synthesis of materials in particulate form, and also includes the methods for production of these systems and intended applications, with a brief description of the most widely used groups following the table.

Table 1. Overview of the materials and methods used for the production of materials in particulate form and envisioned applications (information compiled in the scope of this review)

Material	Type	Method	Application	Description	Ref.
Synthetic polymers and blends					
Poly(lactic acid) (PLA)	Microspheres	o/w solvent evaporation Solvent evaporation Double emulsion technique	Incorporation and release	Release of epidermal growth factor (EGF) Release of somatostatin Release of cisplatin Delivery of antisense oligonucleotides Release of the antischismatic drug N6-cyclophentyladenosine Entrapment of tetanus toxoid for immunization Release of cyclosporine A	(Herrmann and Bodmeier, 1995, 1998; Delle et al., 2001; Han et al., 2001; Dalpiaz et al., 2002; Tamura et al., 2002; Katare et al., 2005)
Poly(lactic acid)/poly(ethylene glycol) (PLA/PEG)	Micro and nanoparticles	Emulsion–solvent evaporation	Incorporation and release		(Gref et al., 2001)
Poly(lactic (PLGA)	Microspheres	Water-in-oil-in-water o/w emulsion solvent evaporation Double emulsion (w/o/w) solvent evaporation ProLease® and spray freeze-drying	Incorporation and release	Release of active lysozyme Release of dexamethasone (DEX) and vascular endothelial growth factor (VEGF) Release of ipriflavone (for osteopenia treatment) Release of enoxacin Release of somatostatin Release of human IgG Release of recombinant human GDNF Release of rIGF1 Release of oligonucleotide for antisense therapy Release of baclofen for spinal spasticity Release of insulin-like growth factor-I (IGF-I)	(Herrmann and Bodmeier, 1998; Cruaud et al., 1999; Abazinge et al., 2000; Lam et al., 2000; Perez et al., 2002; De Rosa et al., 2003; Perugini et al., 2003; Jollivet et al., 2004; Wang et al., 2004; Norton et al., 2005)
	Microspheres	w/o/w–double emulsion–solvent evaporation Water-in-oil-in-water emulsion–extraction–evaporation Multiple emulsion solvent evaporation	Incorporation and release Incorporation and release Carrier for cells Carrier for antigen	Release of parathyroid hormone (PTH) Release of gentamicin Release of bFGF Microcarriers for cells Release of nerve growth factor (NGF) Gene transfer via adenovirus Release of 5-fluorouracil Adjuvant in for immune response Release of acyclovir (for Herpes simplex I) Encapsulation of <i>Brucella ovis</i> antigens for immunization Encapsulation of <i>Helicobacter pylori</i> lysates for immunization Release of bone morphogenetic protein (BMP) Release of VEGF	(Meinel et al., 2001; Singh et al., 2001b; Carrascosa et al., 2004) (Isobe et al., 1996; Yamazaki et al., 1996; Isobe et al., 1999; Walter et al., 1999; King and Patrick, 2000; Kim and Park, 2001; Ain et al., 2002; Hedberg et al., 2002; Murillo et al., 2002; Zhu et al., 2002; Diwan and Park, 2003; Jalón et al., 2003; Perets et al., 2003; Sanchez et al., 2003; Schlapp and Fries, 2003; García Del Barrio et al., 2004; Matzelle and Babensee, 2004; Siepmann et al., 2004; Wei et al., 2004; Tataru et al., 2005)

Copyright © 2007 John Wiley & Sons, Ltd. *J Tissue Eng Regen Med* 2007; 1: 000–000.
DOI: 10.1002/term

Table 1. (Continued)

Material	Type	Method	Application	Description	Ref.
Poly(methyl methacrylate) (PMMA)	Microparticles	o/w solvent evaporation Dispersion polymerization Suspension radical co-polymerization	Entrapment and release	Release of verapamil Delivery of HIV-1 Tat protein for vaccination applications Buformin tosylate – a classical hypoglycaemic drug Release of insulin	(Streubel et al., 2002) (Fundueanu et al., 2001; Caputo et al., 2004)
Poly(methacrylic acid-g-ethylene glycol) P(MAA-g-EG)	Microparticles	Free-radical solution polymerization	Entrapment and release	Release of insulin	(Morishita et al., 2002)
Poly(trimethylene carbonate)-poly(ethylene glycol)-poly(trimethylene carbonate) (PTC-PEG-PTC)	Nanoparticles	Dialysis	Incorporation and release	Release of methotrexate (anticancer drug)	(Zhang and Zhuo, 2005)
Polyvinylpyrrolidone (PVP)	Nanoparticles	Polymerization	Carrier for antigen	Delivery of the antigen of <i>Aspergillus fumigatus</i> for immune system response	(Madan et al., 1997)
Polyvinyl alcohol (PVA/P(Vpi/Vac)	Microparticles Nanoparticles	Suspension polymerization	Embolic materials	Introduced through catheters in the management of gastrointestinal bleeders, traumatic rupture of blood vessels	(Lyo et al., 2002)
Poly(diethylaminoethyl-g-ethylene glycol)	Microparticles	Suspension polymerization	Incorporation	Incorporation of glucose oxidase for treatment of diabetes	(Podual et al., 2000)
ϵ -Polycaprolactone (ϵ -PCL)	Microparticles	Reverse micelle solvent evaporation Simple and double emulsion-solvent evaporation	Incorporation and release	Release of superoxide dismutase Release of nitrofurantoin (antibacterial agent) Release of vancomycin Release of fludrocortisone acetate for hormonal therapy	(Dubertnet et al., 1997; Pérez et al., 2000; Gibaud et al., 2002a, 2002b; Le Ray et al., 2003; Schaffazick et al., 2003; Youan, 2003; Gibaud et al., 2004)
	Nanoparticles	Nanoprecipitation		Release of diclofenac Nifedipine (calcium antagonist) and propranolol HCl (β -blocker), for treatment of hypertension Melarsoprol for the treatment of human trypanosomiasis Release of 3,4-diaminopyridine (3,4-DAP) for multiple sclerosis and Lambert-Eaton myasthenia syndrome	
Poly- ϵ -caprolactone/poly(methyl methacrylate)	Microparticles	Suspension polymerization	N.A.	N.A.	(Abraham et al., 2002)
Poly- ϵ -caprolactone/poly(ethylene glycol)	Nanoparticles	Polymerization and precipitation	Encapsulation and release	Release of all-trans-retinoic acid	(Jeong et al., 2004)
D- α -tocopheryl polyethylene glycol 1000 succinate/poly- ϵ -caprolactone	Microparticles	Double emulsion followed by spray drying	Incorporation and release	Nasal immunization with diphtheria toxoid	(Somavarapu et al., 2005)
Polystyrene	Microparticles	Emulsion solvent evaporation	Incorporation and release	Release of ibuprofen Release of indomethacin	(Tamilvanan and Sa, 2000a, 2000b)
Cytoline 2 [®] (polyethylene and silica)	Microparticles	N.A.	Carrier of antigen	Adjuvant for immune response	(Matzelle and Babensee, 2004)
Natural polymers and blends			Carrier for cell culture	Culture of hybridomas (anti-neuroblastoma monoclonal antibodies)	(Voigt and Zintl, 1999)

Alginate	Beads	Physical crosslinking of calcium ions to sodium alginate polymer (gelation) by needle extrusion	Incorporation and release	Release of bFGF	(Berthold et al., 1998; Chinen et al., 2003; Gu et al., 2004)
	Microparticles	Atomization and gelation using Ca^{2+}	Carrier for cells	Release of glucocorticosteroids	
		Microemulsion	Purification	Release of VEGF	
		Gelation using micro-nozzle array	Incorporation and release	Encapsulation of cells for angiogenic factors release	(Coppi et al., 2002; Safarikova et al., 2003; Keshaw et al., 2005;
		Spray drying		Magnetic affinity adsorbents for purification of enzymes	Rodrigues et al., 2005; Sugiura et al., 2005; Tu et al., 2005)
		Spray-coagulation method		Cell encapsulation of human kidney 293 cells	
				Release of L-lactate dehydrogenase enzyme	
				Release of model compounds	
	Microspherical hydrogels (microspheres)	Gelation using Ca^{2+}	Carrier for vaccines	Incorporation of <i>Aeromonas hydrophila</i> for fish oral vaccination	
		Emulsion crosslinking	Incorporation and release	Delivery of several vaccines	(Bowersock et al., 1996; Kidane et al., 2001; Arica et al., 2005;
	Microparticles	N.A.		Incorporation of glucose oxidase for biosensors	Brown et al., 2005)
Alginate-heparin	Microparticles	N.A.	Incorporation and release	Delivery of ibuprofen	
Alginate-poly-L-lysine	Microparticles	N.A.	Incorporation and release	Release of bFGF	(Chinen et al., 2003)
		Air atomization		Release of NGF	(Maysinger, Jalsenjak et al., 1992;
		Gelation with Ca^{2+} and crosslink		Encapsulation of bifidobacteria for food applications	Cui et al., 2000; Ferreira et al., 2002)
Alginate-poly-L-ornithine	Capsules	Gelation with Ca^{2+}	Incorporation and release	Release of antisense oligonucleotides	
			Carrier for cells	Simultaneous incorporation of ketoprofen-loaded microspheres and rat pancreatic islets	(Ricci et al., 2005)
Alginate-carboxymethyl chitin	Beads	Dropping the solution into an iron solution	Incorporation and release	Release of model compound (albumin)	(Shi et al., 2005)
Alginate-protamine	Microcapsules	Layer-by-layer adsorption of Na alginate and protamine to surface of melamine formaldehyde microparticles	Incorporation and release	Release of α -chymotrypsin, a proteolytic enzyme	(Tiourina and Sukhorukov, 2002)
		Thermal gelation			
Alginate-agarose	Microcapsules	Spraying-ionic crosslinking	Carrier of cells	Cell encapsulation (BHK fibroblast and C_2C_{12} myoblast)	(Orive et al., 2003)
Alginate-chitosan	Microparticles		Incorporation and release	Release of bDNF	(Mittal et al., 1994; Misirli et al., 2005)
Chitosan-coated alginate				Incorporation of mytomycin-C for chemoembolization	
Amphiphilic cyclodextrins	Nanoparticles	N.A.	Encapsulation and release	Release of steroids	(Duchêne et al., 1999)
Chitosan	Microspheres	Emulsion-ionic cross-linking	Incorporation and release	Release of tetracycline	(Ganza-Gonzalez et al., 1999; Lim et al., 2000; van der Lubben et al., 2001; Ko et al., 2002; Yenice et al., 2002)
	Microparticles	Spray drying		Release of metoclopramide for emesis prevention	
		Emulsion-solvent evaporation		Release of gentamicin	
		Precipitation with sodium sulphate		Release of model agent ovalbumin	
		Crosslinking with TPP		Release of model drug felodipine	
	Nanoparticles	Iontropic gelation with polyanion incorporation	Incorporation and release	Release of insulin for intestinal absorption	(Janes et al., 2001b; Mao et al., 2001; Pan et al., 2002)
Chitosan-poly(acrylic acid)				Release of doxorubicin (anticancer agent)	
Chitosan-poly(methyl vinyl ether-co-maleic anhydride) (CH-PVM/MA)	Nanoparticles	Template polymerization	DNA carriers		
	Microparticles	Spray drying	Release of silk peptide		(Hu et al., 2002)
			Propranolol hydrochloride (β -blocker)		(Cerchiara et al., 2005)

Table 1. (Continued)

Material	Type	Method	Application	Description	Ref.
HSA (human serum albumin)	Nanoparticles	Coacervation Desolvation	Incorporation and release Incorporation and release	Release of TGF β 1 Release of betamethasone Release of antisense oligonucleotides	(Huang et al., 2003; Lee et al., 2004; Wartlick et al., 2004)
HSA–magnetite	Particles	N.A.	Incorporation/adsorption and release	Release of antisense oligonucleotides	(Arnedo et al., 2002; Wartlick et al., 2004)
Hyaluronan and derivatives	Microspheres Microparticles Microspheres	N.A. Solvent evaporation Spray drying	Incorporation and release Incorporation and release	Release of dexamethasone Release of pilocarpine Delivery of inactivated influenza vaccines	(Ghassabian et al., 1996) (Zimmer et al., 1994; Singh et al., 2001a)
Gelatin	Microparticles	Coacervation/phase separation Crosslinking Emulsification and crosslinking	Incorporation and release Encapsulation and release Carrier for cell culture	Release of model drugs (metronidazole, prednisolone, cromolyn) Encapsulation of bone stromal cells Release of TGF β 1 Microcarrier for the culture of human nasal chondrocytes Porogen for the formation of foams Release of TGF β 2	(Payne et al., 2002a, 2002b; Holland et al., 2003; Malda et al., 2003a; Esposito et al., 2005)
Collagen	Microspheres Beads Microparticles	N.A. Chemical crosslinking in a water-in-oil emulsion Liophilization with PEG N.A. Emulsion crosslinking	Pore-forming role Incorporation and release Encapsulation and release Incorporation	Release of methotrexate (cancer drug) Incorporation of an antigen for immunization Carriers for glucocorticoids Delivery of all- <i>trans</i> -retinol Release of gentamicin Release of ivermectin Potential for release of agents of interest Vitamin E, benzalkonium chloride Encapsulation of cells	(Thomson et al., 1998; Morita et al., 2001; Kojima et al., 2004) (Narayani and Rao, 1994) (Berthold et al., 1998; Suckow et al., 2002; Swatschek et al., 2002) (Schlapp and Fries, 2003) (Liu et al.,) (Santinho et al., 1999) (Ducclair et al., 2003) (Rabanel and Hildgen, 2004)
Collagen–PLGA Zein (corn protein) Casein Gladdins	Microparticles (PLGA) Microparticles Microparticles Nanoparticles	Dispersion polymerization Phase separation Coacervation Desolvation (drowning-out precipitation)	Incorporation and release Incorporation and release Incorporation and release	Loading of adriamycin for tumour targeting Microcarrier with cell adhesive peptides for bioartificial liver technology Release of verapamil Release of herbicide 2,4-D	(Na et al., 2003) (Kobayashi et al., 2002) (Streubel et al., 2002; Elbahri and Taverdet, 2005)
Amylopectin	Nanoparticles	Conjugation followed by diafiltration (dialysis, filtration and precipitation)	Encapsulation	Release of liposomes	(Stenekes et al., 2001)
Pullulan acetate–sulphonamide	Microspheres Microspheres	N.A. o/w solvent evaporation	Dialysis Cell carriers	Transplantation of rat adrenal chromaffin cells seeded at the surface of the carrier Culture of cells producing inactivated influenza virus Culture of rabies-virus producing cells for vaccination purposes	(Borlongan et al., 1998) (Genzel et al., 2004) (Frazzati-Gallina et al., 2001)
Cellulose	Microparticles	Water-in-oil-in-water (w/o/w) double-emulsion Emulsion solvent evaporation	Incorporation and release	Release of peptides and proteins Release of a vaccine for a rotavirus Immunization against diphtheria Adjuvant for oral immunization	(Touvinen et al., 2004) (Sturesson and Wikingson, 2000; Wikingson and Sjöholm, 2002; Rydell and Sjöholm, 2004)
Dextran (Cytodex®)	Microspheres	N.A.	Entrapment and release Carriers for cell culture		
Starch–acetate Poly(acryl starch)	Microspheres Microparticles	N.A. Solvent extraction Polymerization in water-in-oil emulsion Water-in oil-emulsion with stabilizing hydrocarbon chains	Incorporation and release Incorporation and release Carrier for antigen		

Starch-PLA	Microparticles	Solvent extraction	Incorporation and release	Release of corticosteroids (DEX and methylprednisolone)	(Silva et al., 2005; Silva et al., submitted)
Curdlan (carboxymethylated)	Nanoparticles	Self assembly	Incorporation and release	Release of PDGF	(Na et al., 2000)
Poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV)	Microparticles	w/o/w double emulsion	Incorporation and release	Release of all-trans-retinoic acid	(Baran and Hasirci, 2000; Sendil et al., 1999)
Poly(γ -methyl-L-glutamate)	Microspheres	Suspension-evaporation	Carrier for cell culture	Encapsulation of catalase and asparaginase	(Kato et al., 2003)
Ceramics	Spherical granules	N.A.	Adsorption and release	Cell culture	(Komlev et al., 2002; Matsumoto et al., 2004)
Hydroxyapatite (HA)	Granules	Wet method	Coating	Potential for release of bone bioactive agents (cytochrome c as model)	(Weng et al., 2002)
	Particles	N.A.	Adsorption and release	Potential for release of bone bioactive agents (cytochrome c as model)	(Komlev et al., 2002; Matsumoto et al., 2004)
	Nanocrystals	N.A.	Adsorption and release	Release of growth hormone	(Guicheux et al., 1997; Domingues et al., 2004)
Bioactive glass	Particles	In situ and ex situ processes	Reconstruction	Tetracycline	(Schepers et al., 1991, 1993; Schepers and Ducheyne, 1997; Schepers et al., 1998; Huygh et al., 2002; Gosain, 2004)
		N.A.		Release of BSA (as a model)	(Day et al., 2004)
			Coating	Dental and periodontal reconstruction	(Demers et al., 2002)
			Adsorption and release	Augmentation of the alveolar ridge	(Zerbo et al., 2005)
				Elevation of the sinus floor	(Moner-Girona et al., 2003)
				Coating of polymer fibres for enhancement of cell adhesion	(Santos et al., 1998; Falaize et al., 1999)
				Release of TGF β 1	(Qiu et al., 1999)
				Maxillary sinus floor augmentation	(looss et al., 2001)
				N.A.	(Sivakumar and Panduranga Rao, 2003)
				Release of BPM-2	(Qiu et al., 1998, 2001)
				Release of vancomycin	(Silva et al., 2004)
				Microcarriers for bone tissue formation in rotating bioreactors	
				Injectable bone substitute with release of vancomycin	
				Gentamicin	
				Microcarriers for bone tissue formation in rotating bioreactors	
				Potential for release of bioactive agents and for scaffold materials	

N.A., information not available; o, oil; w, water.

The use of synthetic polymers as carriers has predominantly focused on polyhydroxyalkanoates (Ueda and Tabata, 2003), in particular poly(α -hydroxy esters), because the material has long been used in sutures (Hollinger *et al.*, 1996; Hollinger and Leong, 1996). The most widely used poly(α -hydroxy ester) polymers for particle-based strategies are polylactide (PLA), polyglycolide (PGA) and their co-polymers (poly-DL-lactide-co-glycolide) (PLGA) (Brekke, 1996; Hollinger and Leong, 1996; Whang *et al.*, 1998). Their widespread use stems from the ability of these materials to serve a multitude of purposes and applications.

PLA nanoparticles, in general, have the advantage to be able to pass through the capillary bed and to be mainly concentrated in the liver (60–90%), spleen and lungs (2–10%) and, to a lesser degree, blood marrow (Kreuter, 1983; Brannon-Peppas, 1995). For PLA nanoparticles injected subcutaneously or intramuscularly, they are able to reside at the injection site until biodegradation yields a certain critical molecular weight that enables removal of the degradation products (Kreuter *et al.*, 1983). These particular traits render these systems very interesting for drug delivery applications. Furthermore, tuning of the biodegradability can be performed by blending PLA and PGA in a co-polymer (PLGA), and by changing the proportion of each of these materials in the co-polymer (Miller *et al.*, 1977; Pillai and Panchagnula, 2001; Grayson *et al.*, 2004), as PLA degrades much slower than PGA. Degradation of PLA and PLGA is known to proceed by hydrolytic scission of the polymer chain and depolymerization is influenced by molecular weight (MW), polydispersity and crystallinity (Weinhold *et al.*, 1998; Li and Wozney, 2001).

Although PLGA represents the 'gold standard' (exemplified by more than 500 patents) of biodegradable polymers, increased local acidity because of breakdown products of these polymers can lead to irritation at the target site and may also be detrimental to the stability of protein bioactive agents (Pillai and Panchagnula, 2001). Additional potential problems with these synthetic materials include poor clearance – particularly for high MW polymers – and chronic inflammatory response (Kirker-Head, 2000; Li and Wozney, 2001). For this reason, research has been focusing on other synthetic materials, such as poly(ϵ -caprolactone) (ϵ -PCL), which was, for instance, found to meet the requirements of a biodegradable reservoir or monolithic device for controlled drug delivery, especially in the contraceptive field (Pitt *et al.*, 1979; Dubertnet *et al.*, 1987).

Polyorthoesters (POE) have been under development since the 1970s, and they are unique among all biodegradable polymers, as choosing appropriate diols or mixture of diols in their synthesis can readily vary many of their properties. A number of applications have been found for this class of polymers, such as delivery of 5-fluorouracil, periodontal delivery systems of tetracycline and pH-sensitive polymer systems for insulin delivery (Zignani *et al.*, 2000; Pillai and Panchagnula, 2001).

Polyanhydrides have been considered to be useful biomaterials as carriers of bioactive agents to various organs of the human body, such as bone tissue, blood vessels, brain and eyes (Kumar *et al.*, 2002). They can be prepared easily from readily available, low-cost resources, can be manipulated to meet desirable characteristics, are biocompatible and degrade *in vivo* into non-toxic diacid counterparts that are eliminated from the body as metabolites (Kumar *et al.*, 2002).

However, synthetic materials do not completely fulfil current needs in terms of biomedical applications, and in recent years many researchers have been turning their research focus to materials of natural origin, as these might obviate several of the drawbacks of synthetic materials.

Polyaminoacids, such as poly(γ -methyl-L-glutamate), that have already shown good biocompatibility, have been investigated for the delivery of low MW compounds (Nathan and Kohn, 1994; Pillai and Panchagnula, 2001). However, their widespread use is limited by their antigenic potentials and some difficulties in the control of release that might arise from the dependence on enzymes for biodegradation.

Collagen, viz. type I collagen, is the most widely used natural polymer and is typically derived from bovine or porcine bone, skin or tendon (Winn *et al.*, 1998). The fact that collagen is of animal origin raises concerns, such as the possibility of transmitting diseases. This is particularly critical for materials from bovine sources, due to malignancies such as bovine spongiform encephalopathy (BSE) and the human variant, Creutzfeldt–Jakob disease (CJD). For this reason, other sources of collagen, such as recombinant forms, are seen as an alternative. Collagen exhibits biodegradability, weak antigenicity and superior biocompatibility (Maeda *et al.*, 1999; Lee *et al.*, 2001). This material is regarded as very promising for the delivery of growth factors, as it was found that an electrostatic interaction was the main driving force for the complexation between acidic gelatin and basic fibroblast growth factor (bFGF) (Lee *et al.*, 2001). Biodegradable collagen-based nanoparticles or nanospheres are thermally stable and readily sterilizable (Rossler *et al.*, 1994; Lee *et al.*, 2001). Moreover, nanoparticles can be taken up by the reticuloendothelial system (Marty *et al.*, 1978) and enable an enhanced uptake of exogenous compounds, such as anti-HIV biologically active agents, by a number of cells, especially macrophages (Bender *et al.*, 1996), which may be an additional advantage of collagen-based nanoparticles as a systemic delivery carrier (Lee *et al.*, 2001). Coupled to a small size and a large surface area, high adsorptive capacity and ability to disperse in water to form a clear colloidal solution, the potential of collagen-based nanoparticles has been demonstrated in their use as a sustained release formulation for anti-microbial agents or steroids (Lee *et al.*, 2001). However, some disadvantages of collagen-based systems include the difficulty of assuring adequate supplies, poor mechanical strength (Friess, 1998) and problems related to the use

of animal origin (especially bovine) collagen due to the possibility of disease transmission. Alternatives to animal origin collagens – those produced by recombinant technologies – still present a high cost.

Hyaluronan (hyaluronic acid), typically derived from rooster combs, is a minor component of bone extracellular matrix (ECM) (Li and Wozney, 2001). It has been used as a carrier for bone morphogenetic proteins (BMPs) and sodium hyaluronate gel was used as the delivery system for bFGF (Li and Wozney, 2001). One advantage of hyaluronic acid is that it is negatively charged and can form ionic bonds with positively charged BMPs to increase affinity. Disadvantages of hyaluronic acid include its rapid resorption unless it is crosslinked or chemically modified to decrease its intrinsic hydrophilicity (Li and Wozney, 2001).

However, the fear that some of these materials might additionally be carriers for diseases has led researchers to find other sources of natural products, mostly originating from plants and produced by microorganisms. These might present additional advantages, such as ready supply, low cost, ability to be processed by several methodologies and ability to tailor their properties.

In this field of polymers from nature, poly(glucoses), such as starch and dextrans, have long been used for encapsulating materials for pharmaceutical, cosmetic or food applications (Shahidi and Han, 1993; Pereswetoff-Morath, 1998; Zeller *et al.*, 1999; Engelmann *et al.*, 2004). *Dextrans* are being actively investigated for sustained delivery of therapeutic and imaging agents, particularly for injectables and colon-specific DDSs. *Starch*-based polymers have been proposed by Reis and Cunha (1995) as materials with potential for biomedical applications, particularly as scaffolds for bone tissue engineering applications (Gomes *et al.*, 2001, 2002), bone cements (Espigares *et al.*, 2002; Boesel *et al.*, 2003) and recently as drug delivery systems (Elvira *et al.*, 2002; Silva *et al.*, 2005). These materials have been shown to be biocompatible *in vitro* (Mendes *et al.*, 2001; Marques *et al.*, 2002), and to possess a good *in vivo* performance (Mendes *et al.*, 2003; Salgado *et al.*, 2005). A very important feature of most natural-origin materials, besides the ones described above, is the reaction of the host to degradation products (in the case of starch, the degradation products are oligosaccharides, which can be readily metabolized to produce energy). Regarding their biodegradability, enzymes typically catalyse the hydrolysis of natural biodegradable polymers, e.g. α -amylase catalyses the hydrolysis of starch, which may constitute a strategy to tailor the biodegradability of the material (Azevedo *et al.*, 2003; Araújo *et al.*, 2004; Touvinen *et al.*, 2004).

Chitosans are promising natural polymers that show biocompatibility, good absorption-enhancing, controlled release (Janes *et al.*, 2001a; Mao *et al.*, 2001; Pillai and Panchagnula, 2001), bioadhesive properties (Pillai and Panchagnula, 2001), as well as cell culture, enzymatic immobilization and chromatograph support (Kumar, 2000). Chitosan is a product of the deacetylation of chitin,

produced with varied degrees of deacetylation, and its use is only limited by the poor solubility or insolubility of chitosan in water (Wang *et al.*, 2002). However, growing attention given to this material for several applications, not only for drug delivery, makes us believe that chitosan holds promise to become a very successful material for biomedical applications.

Another widely used polymer of natural origin is *alginate*, a natural polysaccharide extracted from brown algae and composed of various proportions of β -D-mannuronic acid (M) and α -L-guluronic acid (G) residues. This naturally occurring biopolymer has many applications in various areas of biosciences and biotechnology (e.g. as a matrix for the entrapment and/or delivery of a variety of proteins and cells) and in the food and beverage industry (as a thickening or gelling agent and a colloidal stabilizer) (Smidsrød and Skjåk-Bræk, 1990; Safarikova *et al.*, 2003; Gu *et al.*, 2004). Besides the best-known method to prepare alginate beads – which is a gelation method in which a sodium alginate solution is single-dropped into a calcium solution, forming particles several μm in diameter – several other well-known methods (atomization, spraying and water-in-oil emulsification methods) can also be used to prepare alginate microparticles that are less than 200 μm in diameter (Gombotz and Wee, 1998; Safarikova *et al.*, 2003). Gelation occurs by an ionic interaction between the calcium ions and the carboxylate anions of G–G blocks as calcium ions diffuse from the external source into the droplet (Gu *et al.*, 2004). The main advantage of using alginate is that the alginate gelation process occurs under very mild conditions without using high temperatures or chemical crosslinking agents (Gu *et al.*, 2004), thus allowing the preservation of the viability and biological activity of the entrapped cells and other agents, respectively. However, the application of this system has been limited by poor mechanical stability. Combining alginate with other polymers and ceramic materials has been shown to obviate this feature (Sivakumar and Panduranga Rao, 2003). Recent studies have described a dual function of alginate microparticles as carriers for both cells and drugs, for application in diabetes (Ricci *et al.*, 2005), an idea that we also propose for bone tissue engineering applications using starch-based microparticles (Silva *et al.*, submitted).

Polyhydroxybutyrate is a polyester produced as granules by microorganisms (Fidler and Dennis, 1992; Saito and Doi, 1994; Jung *et al.*, 2005) and has been widely studied for tissue engineering applications (Chen and Wu, 2005), mainly for scaffold materials in combination with ceramic materials (Doyle *et al.*, 1991; Knowles *et al.*, 1992, 1993; Li and Chang, 2004; Li *et al.*, 2005) and also as a vehicle for drug delivery (Koosha and Muller, 1987; Koosha *et al.*, 1989).

Although polymers are seen as the most versatile class of materials, other classes have been widely studied for biomedical applications. Among these are ceramic materials, which are refractory, polycrystalline compounds, composed of ionically bonded compounds (de Groot,

1983; Bajpai and Billote, 1995). Ceramic materials, such as *tricalcium phosphate* (TCP), *hydroxyapatite* (HA) and *bioactive glasses* (BG) have been widely investigated for hard tissue applications (Balla *et al.*, 1991; Schepers *et al.*, 1991, 1993, 1998; Meenen *et al.*, 1992; Gatti *et al.*, 1994; Schepers and Ducheyne, 1997; Chu *et al.*, 2002; Huygh *et al.*, 2002; Artzi *et al.*, 2005; Kim *et al.*, 2005; Chu *et al.*, 2006), for filling, support and promotion of regeneration. Their role as drug delivery devices derives from their compatibility and physical characteristics, such as non-immunogenicity and degradability. Ceramics as drug delivery systems were basically in the form of porous materials and using the well-known ceramics mentioned above. As proposed by Ducheyne and co-workers (Nicoll *et al.*, 1997; Santos *et al.*, 1998, 1999), sol-gel technology for the formation of silica-based xerogels, which allows the introduction of functional proteins into glass-like materials, is a very interesting strategy that couples the bioactive behaviour of these systems with drug delivery capability and the additional ability to tailor other properties. Another major advantages relate to room temperature processing without the need for solvents.

Further details on ceramic materials in bone tissue engineering can be found in the second part of this review (Silva *et al.*, 2006).

5. Applications

Although some applications of materials in particulate form have been mentioned so far, Table 2 lists the major applications of such materials in the biomedical field. By far the greatest field of application for these materials, as found in the literature, is as drug delivery systems (DDS) and a few important principles regarding this field follow.

5.1. Basic concepts in drug delivery

Drug delivery routes are normally four (Langer, 1991; Nitsch and Banakar, 1994): (a) oral, for pills and syrups; (b) rectal; (c) intramuscular or intravenous, for solutions;

and (d) topical, as for eye drops. These conventional systems of drug delivery have a major disadvantage, which is that with time the concentration of the bioactive agent decreases to a minimum, leading to the need for a new dose of bioactive agent within a short time interval. Another problem is that the bioactive agent will be distributed systemically throughout the body of the patient (Langer, 1991; Williams, 1998). In general, for oral drug delivery systems, the major problem is the rapid loss of activity of the therapeutic agent in the hostile environment of the stomach (Ponchel and Irache, 1998; Chellat *et al.*, 2000; Grassi *et al.*, 2001). It has also been observed that chemically attaching a bioactive agent to a polymer (bioactive agent-macromolecule conjugate) may alter such properties as its distribution in the body, rate of appearance in certain tissues, solubility or antigenicity (Langer, 1991; Kumar, 2000).

Since oral drug administration remains the easiest and the most comfortable method (Ponchel and Irache, 1998; Chellat *et al.*, 2000; Pillai *et al.*, 2001; Keegan *et al.*, 2003), the microencapsulation of bioactive agents seemed to be an alternative to overcome the problem, allowing their slow release and protection against the acidic and enzymatic gastric environment (Berthold *et al.*, 1998; Chellat *et al.*, 2000). All these were reasons that led to the development of delivery systems, whose aim is to facilitate the dosage and duration of effect of the bioactive agent, causing minimal harm and improving patient compliance (Langer, 1991; Pillai *et al.*, 2001), since they would allow a reduction of the dosage frequency (Kumar, 2000; Pillai and Panchagnula, 2001).

For drug delivery applications, the development of intravenously administrated carriers with blood circulation times long enough to continuously deliver bioactive compounds (Gref *et al.*, 1994; Hrkach *et al.*, 1997; Berton *et al.*, 1999; Kumar, 2000), imaging agents or other entities to specific sites of action (Gref *et al.*, 1994) has been a major challenge, since these carriers must possess a set of features compatible with the task they are required to perform. The desired features of such a carrier include (Gref *et al.*, 1994; Soppimath *et al.*, 2001):

Table 2. Major applications of materials in particulate form in the biomedical field (information compiled in the scope of this review)

Applications in the biomedical field	References
Chromatography	(Attebery, 1975; Rocca and Rouchouse, 1976; Fahlvik <i>et al.</i> , 1990; Zhang and El Rassi, 1999; Spegel <i>et al.</i> , 2001)
Imaging	(Cuthbertson <i>et al.</i> , 2003; Cavalieri <i>et al.</i> , 2005; Huang <i>et al.</i> , 2006; Klivanov, 2006)
Filling of defects	(Schepers <i>et al.</i> , 1991; Guicheux <i>et al.</i> , 1997; Santos <i>et al.</i> , 1998; Schepers <i>et al.</i> , 1998; Falaize <i>et al.</i> , 1999; Huygh <i>et al.</i> , 2002; Day <i>et al.</i> , 2004; Domingues <i>et al.</i> , 2004; Gosain, 2004)
Adjuvants in vaccines	(Ohagan <i>et al.</i> , 1993; Moore <i>et al.</i> , 1995; Nakaoka <i>et al.</i> , 1995; Ertl <i>et al.</i> , 1996; Heritage <i>et al.</i> , 1996; Ohagan <i>et al.</i> , 1997; Stertman <i>et al.</i> , 2006)
Cell culture	(Malda <i>et al.</i> , 2003b; Xu <i>et al.</i> , 2003; Zhang <i>et al.</i> , 2003; Liu and Wu, 2004; Yokomizo <i>et al.</i> , 2004; Hong <i>et al.</i> , 2005; Melero-Martin <i>et al.</i> , 2006)
Drug delivery	(Herrmann and Bodmeier, 1995; Guicheux <i>et al.</i> , 1997; Berthold <i>et al.</i> , 1998; Herrmann and Bodmeier, 1998; Jeong <i>et al.</i> , 1998; Cruaud <i>et al.</i> , 1999; Ganza-Gonzalez <i>et al.</i> , 1999; Lam <i>et al.</i> , 2000; Lim <i>et al.</i> , 2000; Brigger <i>et al.</i> , 2001; Delie <i>et al.</i> , 2001; Han <i>et al.</i> , 2001; Singh <i>et al.</i> , 2001a, 2001b; van der Lubben <i>et al.</i> , 2001; Dalpiaz <i>et al.</i> , 2002; Demers <i>et al.</i> , 2002; Ko <i>et al.</i> , 2002; Morishita <i>et al.</i> , 2002; Perez <i>et al.</i> , 2002; Tamura <i>et al.</i> , 2002; Yenice <i>et al.</i> , 2002; Chinen <i>et al.</i> , 2003; De Rosa <i>et al.</i> , 2003; Perugini <i>et al.</i> , 2003; Gu <i>et al.</i> , 2004; Jeong <i>et al.</i> , 2004; Jollivet <i>et al.</i> , 2004; Wang <i>et al.</i> , 2004; Norton <i>et al.</i> , 2005; Silva <i>et al.</i> , 2005)

Figure 1. Schematic of the release of entrapped bioactive agents from biodegradable polymeric particles. When the polymer device incorporating the active agent (A) is inserted into the environment, the fluid from the surrounding medium enters the matrix (B), causing swelling of the device (C). The fluid creates diffusion channels (C) and the incorporated active agent is released to the external environment (D). In the case of biodegradable polymers, device removal will occur by degradation of the material

1. That the agent to be encapsulated comprises a reasonably high weight fraction (loading) of the total carrier system (e.g. >30%).
2. The amount of agent used in the first step of the encapsulation process is incorporated into the final carrier (entrapment efficiency) at a reasonably high level (e.g. >80%).
3. The ability to be freeze-dried and reconstituted in solution without aggregation.

4. Biodegradability.
5. Small size.
6. Characteristics to prevent rapid clearance of the particles from the bloodstream.

Also, within drug delivery systems, it is essential to distinguish between sustained and controlled delivery systems, as these two types denote very different applications. *Sustained* systems imply that the bioactive agent is delivered over a prolonged period of time to overcome the highly periodic nature of tissue levels associated with conventional (enteral or parenteral) administration of single doses by tablets or fluids (Langer, 1991; Silvio *et al.*, 1994; Williams, 1998). The term 'controlled' is used generically to indicate any device in which some control is exerted over the way in which the bioactive agent is delivered to the tissues once it has been administered to the patient (Langer, 1991; Silvio *et al.*, 1994; Williams, 1998). This is best exemplified in the concept of thermally and pH-responsive materials, where variation in the temperature/pH discontinuously or sharply changes properties such as volume (De Jaeghere *et al.*, 2000; Kawaguchi, 2000; Morishita *et al.*, 2002). This concept is extremely important, as it can be used as a means to trigger the release of the entrapped bioactive agent, and thus allow control to be exerted over the system.

If other ways of controlling the system can be developed, besides temperature and pH, e.g. the presence of a certain agent would trigger the release of the incorporated agent, this could be used for other applications. One such application has been described by Cavanaugh *et al.* (2001), in which the microparticles released their load of adenovirus only upon cell contact, thus preventing inactivation of the viral load.

5.2. Polymers as the primary choice for DDS

The class of materials that has been most widely studied for drug delivery applications is the polymeric one.

Polymeric delivery systems generally release bioactive agents by the following mechanisms (Langer, 1991; Chellat *et al.*, 2000): diffusion, chemical reaction or solvent activation. The release of a bioactive agent from a matrix is primarily controlled by diffusion of the bioactive agent through the polymer, erosion of the polymer being an additional but important factor (Grassi *et al.*, 2001). For biodegradable polymers, degradation is a chemical process, whereas erosion is a physical phenomenon dependent on dissolution and diffusion processes. As soon as the bioactive agent-containing polymer (A) comes into contact with the external liquid environment, it enters the polymer matrix (B), resulting in a swelling process (C), which allows the diffusion of the bioactive agent into the external environment (Grassi *et al.*, 2001) (D), as illustrated in Figure 1. Factors influencing the release rate include the molecular size of the bioactive agent and loading percentage into the polymer, as well as polymer composition, molecular weight and the dimensions and shape of the matrix (Langer, 1991).

There are usually three distinct phases of release for biodegradable polymers (as shown in Figure 2):

1. A burst or initial period of rapid diffusion of active agent located close to the surface of the polymer.
2. A period of minimal release, during which the polymer is gradually hydrolysed in bulk but has not yet decreased sufficiently in molecular weight to allow an increased diffusional release of the active agent.

Figure 2. Release profile for biodegradable polymers. The first stage (1) is a burst release, caused by diffusion of the bioactive agent located closer to the surface. The second stage (2) is caused by gradual degradation of the polymer, and the third stage (3) is characterized by massive degradation (solubilization) of the material

3. The molecular weight of the polymer is sufficiently low as to allow its solubilization in the aqueous environment, and the release of the remaining active agent occurs as the polymer is eroded (Weinhold *et al.*, 1998; Berkland *et al.*, 2002).

This release profile is generally regarded as a problem common to many biodegradable systems, where the release is dependent upon degradation of the system with time (Silvio *et al.*, 1994), thus there is no possibility of achieving any kind of control. This type of device is therefore more suitable for sustained rather than controlled release.

In short, and for drug delivery systems in general, the bulk properties of the polymer that need to be considered include (Langer, 1991; Pillai and Panchagnula, 2001):

- Molecular weight.
- Physical properties (bioadhesiveness, mechanical stability).
- Solubility based on the release mechanism (diffusion or dissolution-controlled).
- Site of action.

Bioadhesiveness needs to be taken into account when drug delivery systems are targeted to mucosal tissues, whereas polymers for ocular devices have to be water- or lipid-soluble in addition to having good film-forming ability and mechanical stability for good retention. The structural properties of the matrix, its micromorphology and pore size, are important with respect to mass transport (of water) into and (of bioactive agent) out of the polymer (Pillai and Panchagnula, 2001).

Of great importance, however, is the assurance that the biological activity of the incorporated agent is preserved throughout manufacturing, storage, delivery and release (King and Patrick, 2000). This, together with the release profile, is of particular importance when designing a delivery system, because much as the release profile may be adequate, there is no point in having it if the biological activity of the agent to be delivered is lost during processing. This idea is mostly coupled with the use of solvents in the production of the delivery system because, as mentioned before, organic solvents might cause inactivation of the agent to be loaded into the system. For growth factors, BSA has been shown to be protective when used as an adjuvant during the loading process (Kim and Valentini, 1997; Morlock *et al.*, 1998), but methods that obviate this step are needed.

Regarding the release profile, strategies to control or render it more adequate for a particular application, by means of modifying parameters such as the surface (by coating, chemical modification) or creating dual-release systems (layers of materials that can incorporate different molecules) (Kim and Valentini, 1997; Vaz *et al.*, 2004), can greatly improve the properties of several materials, and should be actively pursued.

6. Conclusions

Materials in the particulate form have been employed in a diversity of biomedical applications. This derives from their properties, such as size, surface area, and physicochemical properties, which stem from the diverse materials and methods combined for their production. Within the range of applications, drug delivery has had a highlighted role, because of its promise as a means of overcoming limitations inherent to conventional delivery methods. Currently, the use of these systems in innovative strategies, where they can play a multitude of roles – delivery of bioactive agents, structural support and carriers of cells – makes it mandatory for researchers to become even more creative in developing such a system. Within this perspective, an area of tissue engineering that can obviously benefit from the specific properties of materials in particulate form is bone tissue engineering.

Part B of this review (this issue) deals with the roles – played and potential – of particle-based systems in this specific subset of tissue engineering applications, bone tissue engineering.

Acknowledgements

The Portuguese Foundation for Science and Technology (FCT) is acknowledged for a PhD grant to G.A.S (SFRH/BD/4698/2001). This work was partially supported by FCT through funds from the POCTI and/or FEDER, European Union-funded STREP Project Hippocrates (NNM-3-CT-2003-505758) and the European NoE EXPERTISSUES (NMP3-CT-2004-500283).

References

- Abazinge M, Jackson T *et al.* 2000; *In vitro* and *in vivo* characterization of biodegradable enoxacin microspheres. *Eur J Pharmaceut Biopharmaceut* **49**(2): 191–194.
- Abraham GA, Kesenci K *et al.* 2002; Microcomposites of poly(ϵ -caprolactone) and poly(methyl methacrylate) prepared by suspension polymerization in the presence of poly(ϵ -caprolactone) macromonomer. *Macromol Mater Eng* **287**(12): 938–945.
- Ain Q, Sharma S *et al.* 2002; Role of poly [ϵ -lactide-co-glycolide] in development of a sustained oral delivery system for antitubercular drug(s). *Int J Pharmaceut* **239**(1–2): 37.
- Allemann E, Leroux JC *et al.* 1998; Polymeric nano- and microparticles for the oral delivery of peptides and peptidomimetics. *Adv Drug Delivery Rev* **34**: 171–189.
- Araújo MA, Cunha AM *et al.* 2004; Enzymatic degradation of starch based thermoplastic compounds used in prostheses. *Mater Sci Forum* **455–456**: 429–432.
- Arica B, Calis S *et al.* 2005; *In vitro* and *in vivo* studies of ibuprofen-loaded biodegradable alginate beads. *J Microencapsulation* **22**(2): 153–165.
- Arnedo A, Espuelas S *et al.* 2002; Albumin nanoparticles as carriers for a phosphodiester oligonucleotide. *Int J Pharmaceut* **244**: 59–72.
- Artzi Z, Kozlovsky A *et al.* 2005; The amount of newly formed bone in sinus grafting procedures depends on tissue depth as well as the type and residual amount of the grafted material. *J Clin Periodontol* **32**(2): 193–199.
- Attetbery JA. 1975; Use of microparticles for preparative liquid chromatography. *Chromatographia* **8**(3): 121–123.
- Azevedo HS, Gama FM *et al.* 2003; *In vitro* assessment of the enzymatic degradation of several starch-based biomaterials. *Biomacromolecules* **4**(6): 1703–1712.

- 1 Bajpai PK, Billote W. 1995; Ceramic biomaterials. In *Biomedical Engineering Handbook*, Bronzino JD (ed.). CRC Press: Boca Raton, FL; 552.
- 2 Baldwin SP, Saltzman WM. 1998; Materials for protein delivery in tissue engineering. *Adv Drug Delivery Rev* **33**(1–2): 71–86.
- 3 Balla R, Lomonaco CJ *et al.* 1991; Histological study of furcation perforations treated with tricalcium phosphate, hydroxyapatite, amalgam, and •life. *J Endodont* **17**(5): 234–238.
- 4 Baran E, •Hasirci V. •••••
- 5 Bender A, von Briesen H *et al.* 1996; Efficiency of nanoparticles as a carrier system for antiviral agents in human monocytes/macrophages *in vitro*. *Antimicrob Agents Chemother* **40**: 1467–1471.
- 6 Berkland C, King M *et al.* 2002; Precise control of PLG microsphere size provides enhanced control of drug release rate. *J Controlled Release* **82**: 137–147.
- 7 Berthold A, Cremer K *et al.* 1998; Collagen microparticles: carriers for glucocorticosteroids. *Eur J Pharmaceut Biopharmaceut* **45**: 23–29.
- 8 Berton M, Allemann E *et al.* 1999; Highly loaded nanoparticulate carrier using an hydrophobic antisense oligonucleotide complex. *Eur J Pharmaceut Sci* **9**(2): 163–170.
- 9 Bezemer JM, Radersma R *et al.* 2000a; Microspheres for protein delivery prepared from amphiphilic multiblock co-polymers 1. Influence of preparation techniques on particle characteristics and protein delivery. *J Controlled Release* **67**: 233–248.
- 10 Bezemer JM, Radersma R *et al.* 2000b; Microspheres for protein delivery prepared from amphiphilic multiblock co-polymers 2. Modulation of release rate. *J Controlled Release* **67**(2–3): 249–260.
- 11 Birnbaum D, Kosmala J *et al.* 2000; Controlled release of β -estradiol from PLGA microparticles: the effect of organic phase solvent on encapsulation and release. *J Controlled Release* **65**: 375–387.
- 12 Bissery MC, Valeriote F *et al.* 1984; *In vitro* and *in vivo* evaluation of CCNU-loaded microspheres prepared from poly($\pm$ -lactide) and poly(β -hydroxybutyrate). In *Microspheres and Drug Therapy: Pharmaceutical, Immunological and Medical Aspects*, Davis I, •McVie •, Tomlinson • (eds). Elsevier Science: Amsterdam.
- 13 Boesel LF, Mano JF *et al.* 2003; Hydrogels and hydrophilic partially degradable bone cements based on biodegradable blends incorporating starch. In *Biodegradable Polymers and Plastics*, Chiellini E (ed.). Kluwer Academic: Dordrecht.
- 14 Borlongan CV, Saporta S *et al.* 1998; Intrastriatal transplantation of rat adrenal chromaffin cells seeded on microcarrier beads promote long-term functional recovery in hemiparkinsonian rats. *Exp Neurol* **151**: 203–214.
- 15 Bowersock TL, HogenEsch H *et al.* 1996; Oral vaccination with alginate microsphere systems. *J Controlled Release* **39**: 209–220.
- 16 Brannon-Peppas L. 1995; Recent advances on the use of biodegradable microparticles and nanoparticles in controlled drug delivery. *Int J Pharmaceut* **116**: 1–9.
- 17 Brasseur N, Brault D *et al.* 1991; Adsorption of haematoporphyrin onto polyalkylcyanoacrylate nanoparticles: carrier capacity and drug release. *Int J Pharmaceut* **70**: 129–135.
- 18 Brekke JH. 1996; A rationale for delivery of osteoinductive proteins. *Tissue Eng* **2**: 97–114.
- 19 Brigger I, Chaminade P *et al.* 2001; Tamoxifen encapsulation within polyethylene glycol-coated nanospheres. A new antiestrogen formulation. *Int J Pharmaceut* **214**(1–2): 37–42.
- 20 Brigger I, Dubernet C *et al.* 2002; Nanoparticles in cancer therapy and diagnosis. *Adv Drug Delivery Rev* **54**(5): 631–651.
- 21 Brown JQ, Srivastava R *et al.* 2005; Encapsulation of glucose oxidase and an oxygen-quenched fluorophore in polyelectrolyte-coated calcium alginate microspheres as optical glucose sensor systems. *Biosens Bioelectron* **21**(1): 212–216.
- 22 Buntner B, Nowak M *et al.* 1998; The application of microspheres from the co-polymers of lactide and [epsilon]-caprolactone to the controlled release of steroids. *J Controlled Release* **56**(1–3): 159–167.
- 23 Caputo A, Cofano EB *et al.* 2004; Novel biocompatible anionic polymeric microspheres for the delivery of the HIV-1 Tat protein for vaccine application. *Vaccine* (in press).
- 24 Carrascosa C, Torres-Aleman I *et al.* 2004; Microspheres containing insuling-like growth factor I for treatment of chronic neurodegeneration. *Biomaterials* **25**: 707–714.
- 25 Cavalieri F, El Hamassi A *et al.* 2005; Stable polymeric microballoons as multifunctional device for biomedical uses: synthesis and characterization. *Langmuir* **21**(19): 8758–8764.
- 26 Cavanagh HMA, Dingwall D *et al.* 2001; Cell contact dependent extended release of adenovirus by microparticles *in vitro*. *J Virol Methods* **95**(1–2): 57.
- 27 Cerchiara T, Luppi B *et al.* 2005; Chitosan and poly(methyl vinyl ether-co-malei anhydride microparticles as nasal sustained delivery systems. *Eur J Pharmaceut Biopharmaceut* (in press).
- 28 Chellat F, Tabrizian M *et al.* 2000; Study of biodegradation behaviour of chitosan-xanthan microspheres in simulated physiological media. *J Biomed Mater Res* **53**: 592–599.
- 29 Chen GQ, Wu Q. 2005; The application of polyhydroxyalkanoates as tissue engineering materials. *Biomaterials* **26**(33): 6565–6578.
- 30 Chinen N, Tanihara M *et al.* 2003; Action of microparticles of heparin and alginate crosslinked gel when used as injectable artificial matrices to stabilize basic fibroblast growth factor and induce angiogenesis by controlling its release. *J Biomed Mater Res* **67**: 61–68.
- 31 Chu C, Lin P *et al.* 2002; Fabrication and characterization of hydroxyapatite reinforced with 20 vol% Ti particles for use as hard tissue replacement. *J Mater Sci Mater Med* **13**(10): 985–992.
- 32 Chu CL, Xue XY *et al.* 2006; Fabrication and characterization of titanium-matrix composite with 20 vol% hydroxyapatite for use as heavy load-bearing hard tissue replacement. *J Mater Sci Mater Med* **17**(3): 245–251.
- 33 Coppi G, Iannuccelli V *et al.* 2002; Alginate microparticles for enzyme peroral administration. *Int J Pharmaceut* **242**: 263–266.
- 34 Couvreur P, Puisieux F. 1993; Nano- and microparticles for the delivery of polypeptides and proteins. *Adv Drug Delivery Rev* **10**: 141–162.
- 35 Cruaud O, Benita S *et al.* 1999; The characterization and release kinetics evaluation of baclofen microspheres designed for intrathecal injection. *Int J Pharmaceut* **177**(2): 247.
- 36 Cui J-H, Goh J-S *et al.* 2000; Survival and stability of bifidobacteria loaded in alginate poly-L-lysine microparticles. *Int J Pharmaceut* **210**(1–2): 51.
- 37 Cuthbertson A, Tornes A *et al.* 2003; Amphiphilic lipopeptide microparticles as contrast agents for medical ultrasound imaging. *Macromol Biosci* **3**(1): 11–17.
- 38 Dalpiaz A, Scatturin A *et al.* 2002; Poly(lactic acid) microspheres for the sustained release of antiischemic agents. *Int J Pharmaceut* **242**: 115–120.
- 39 Day RM, Boccacini AR *et al.* 2004; Assessment of polyglycolic acid mesh and bioactive glass for soft-tissue engineering scaffolds. *Biomaterials* **25**: 5857–5866.
- 40 de Groot K. 1983; *Ceramics of Calcium Phosphates: Preparation and Properties*. CRC Press: Boca Raton, FL; 99.
- 41 De Jaeghere F, Allemann E *et al.* 2000; Oral bioavailability of a poorly water soluble HIV-1 protease inhibitor incorporated into pH-sensitive particles: effect of the particle size and nutritional state. *J Controlled Release* **68**(2): 291.
- 42 De Rosa G, Bochot A *et al.* 2003; A new delivery system for antisense therapy: PLGA microspheres encapsulating oligonucleotide/polyethyleneimine solid complexes. *Int J Pharmaceut* **254**(1): 89–93.
- 43 Delie F, Berton M *et al.* 2001; Comparison of two methods of encapsulation of an oligonucleotide into poly-(lactic acid) particles. *Int J Pharmaceut* **214**(1–2): 25.
- 44 Demers C, Tabrizian M *et al.* 2002; Effects of experimental parameters on the *in vitro* release kinetics of transforming growth factor β 1 from coral particles. *J Biomed Mater Res* **59**: 403–410.
- 45 Diwan M, Park TG. 2003; Stabilization of recombinant interferon- α by pegylation for encapsulation in PLGA microspheres. *Int J Pharmaceut* **252**(1–2): 111–122.
- 46 Domingues ZR, Cortes ME *et al.* 2004; Bioactive glass as a drug delivery system of tetracycline and tetracycline associated with β -cyclodextrin. *Biomaterials* **25**(2): 327.
- 47 Doyle C, Tanner ET *et al.* 1991; *In vitro* and *in vivo* evaluation of polyhydroxybutyrate and of polyhydroxybutyrate reinforced with hydroxyapatite. *Biomaterials* **12**(9): 841–847.
- 48 Dubernet C, Benoit JP *et al.* 1987; Microencapsulation of nitrofurantoin in poly(ϵ -caprolactone) tableting and *in vitro* release studies. *Int J Pharmaceut* **35**: 145–156.
- 49 Duchêne D, Wouessidjewe D *et al.* 1999; Cyclodextrins and carrier systems. *J Controlled Release* **62**: 263–268.
- 50 Duclairoir C, Orecchioni A-M *et al.* 2003; Evaluation of gliadins nanoparticles as drug delivery systems: a study of three different drugs. *Int J Pharmaceut* **253**: 133–144.
- 51 Elbahri Z, Taverdet JL. 2005; Optimization of an herbicide release from ethylcellulose microspheres. *Polym Bull* **54**(4–5): 353–363.

- 1 Eliaz RE, Kost J. 2000; Characterization of a polymeric PLGA-injectable implant delivery system for the controlled release of proteins. *J Biomed Mater Res* **50**: 388–396.
- 2 Elvira C, Mano JF et al. 2002; Starch-based biodegradable hydrogels with potential biomedical applications as drug delivery systems. *Biomaterials* **23**(9): 1955–1966.
- 3 Engelmann G, Jobmann M et al. 2004; Dextran carbamates – materials for microencapsulation. *Indust Crops Products* (in press).
- 4 Ertl HCJ, Varga I et al. 1996; Poly(DL-lactide-co-glycolide) microspheres as carriers for peptide vaccines. *Vaccine* **14**(9): 879–885.
- 5 Espigares I, Elvira C et al. 2002; New partially degradable and bioactive acrylic bone cements based on starch blends and ceramic fillers. *Biomaterials* **23**(8): 1883–1895.
- 6 Esposito E, Menegetti E et al. 2005; Hyaluronan-based microparticles as tools for delivery: a comparative study. *Int J Pharmaceut* **288**(1): 35–49.
- 7 Fahlvik AK, Artursson P et al. 1990; Magnetic starch microspheres – interactions of a microsphere M_r contrast medium with macrophages *in vitro*. *Int J Pharmaceut* **65**(3): 249–259.
- 8 Falaize S, Radin S et al. 1999; *In vitro* behaviour of silica-based xerogels intended as controlled release carriers. *Journal Am Ceram Soc* **82**(4): 969–976.
- 9 Fawaz F, Guyot M et al. 1997; Ciprofloxacin-loaded polyisobutylcyanoacrylate nanoparticles: preparation and characterization. *Int J Pharmaceut* **154**: 191–203.
- 10 Ferreiro MG, Tillman L et al. 2002; Characterization of alginate/poly-L-lysine particles as antisense oligonucleotide carriers. *Int J Pharmaceut* **239**: 47–59.
- 11 Fidler S, Dennis D. 1992; Polyhydroxyalkanoate production in recombinant *Escherichia coli*. *FEMS Microbiol Rev* **103**(2–4): 231–235.
- 12 Frazzati-Gallina NM, Paoli RL et al. 2001; Higher production of rabies virus in serum-free medium cell cultures on microcarriers. *J Biotechnol* **92**: 67–72.
- 13 Friess W. 1998; Collagen-biomaterial for drug delivery. *Eur J Pharmaceut Biopharmaceut* **45**: 113–136.
- 14 Fundueanu G, Mocanu G et al. 2001; Acrylic microspheres for oral controlled release of the biguanide buformin. *Int J Pharmaceut* **218**(1–2): 13.
- 15 Ganza-Gonzalez A, Anguiano-Igea S et al. 1999; Chitosan and chondroitin microspheres for oral-administration controlled release of metoclopramide. *Eur J Pharmaceut Biopharmaceut* **48**(2): 149.
- 16 Gaspar MM, Blanco D et al. 1998; Formulation of L-asparaginase-loaded poly(lactide-co-glycolide) nanoparticles: influence of polymer properties on enzyme loading, activity and *in vitro* release. *J Controlled Release* **52**: 53–62.
- 17 Gatti AM, Valdre G et al. 1994; Analysis of the *in vivo* reactions of a bioactive glass in soft and hard tissue. *Biomaterials* **15**(3): 208–212.
- 18 Genzel Y, Behrendt I et al. 2004; Metabolism of MDCK cells during cell growth and influenza virus production in large-scale microcarrier culture. *Vaccine* **22**: 2202–2208.
- 19 Ghaderi R, Artursson P et al. 1999; Preparation of biodegradable microparticles using solution-enhanced dispersion by supercritical fluids (SEDS). *Pharmaceut Res* **16**: 676–681.
- 20 Ghassabian S, Ehtezazi T et al. 1996; Dexamethasone-loaded magnetic albumin microspheres: preparation and *in vitro* release. *Int J Pharmaceut* **130**: 49–55.
- 21 Gibaud S, Al Awwadi NJ et al. 2004; Poly(ϵ -caprolactone) and Eudragit® microparticles containing fludrocortisone acetate. *Int J Pharmaceut* **269**: 491–508.
- 22 Gibaud S, Bonneville A et al. 2002a; Preparation of 3,4-diaminopyridine microparticles by solvent-evaporation methods. *Int J Pharmaceut* **242**: 197–201.
- 23 Gibaud S, Gaia A et al. 2002b; Slow-release melarsoprol microparticles. *Int J Pharmaceut* **243**: 161–166.
- 24 Gombotz WR, Wee S. 1998; Protein release from alginate matrices. *Adv Drug Delivery Rev* **31**: 267–285.
- 25 Gomes ME, Godinho JS et al. 2002; Alternative tissue engineering scaffolds based on starch: processing methodologies, morphology, degradation and mechanical properties. *Mater Sci Eng C-Biomimet Supramol Syst* **20**(1–2): 19–26.
- 26 Gomes ME, Ribeiro AS et al. 2001; A new approach based on injection moulding to produce biodegradable starch-based polymeric scaffolds: morphology, mechanical and degradation behaviour. *Biomaterials* **22**(9): 883–889.
- 27 Gosain AK. 2004; Bioactive glass for bone replacement in craniomaxillofacial reconstruction. *Plastic Reconstruct Surg* **114**(2): 590–593.
- 28 Grassi M, Colombo I et al. 2001; Experimental determination of the theophylline diffusion coefficient in swollen sodium-alginate membranes. *J Controlled Release* **76**(1–2): 93–105.
- 29 Grayson ACR, Voskerician G et al. 2004; Differential degradation rates *in vivo* and *in vitro* of biocompatible poly(lactic acid) and poly(glycolic acid) homo- and co-polymers for a polymeric drug-delivery microchip. *J Biomater Sci* **15**(10): 1281–1304.
- 30 Gref R, Minamitake Y et al. 1994; Biodegradable long-circulating polymeric nanospheres. *Science* **263**: 1600–1603.
- 31 Gref R, Quellec P et al. 2001; Development and characterization of CyA-loaded poly(lactic acid)-poly(ethylene glycol) PEG micro- and nanoparticles. Comparison with conventional PLA particulate carriers. *Eur J Pharmaceut Biopharmaceut* **51**(2): 111.
- 32 Gu F, Amsden B et al. 2004; Sustained delivery of vascular endothelial growth factor with alginate beads. *J Controlled Release* **96**: 463–472.
- 33 Guicheux J, Grimandi G et al. 1997; Apatite as carrier for growth hormone: *in vitro* characterization of loading and release. *J Biomed Mater Res* **34**: 165–170.
- 34 García Del Barrio G, Hendry J et al. 2004; *In vivo* sustained release of adenoviral vectors from poly(D,L-lactide-co-glycolic) acid microparticles prepared by TROMS. *J Controlled Release* **94**(1): 229–235.
- 35 Han K, Lee KD et al. 2001; Preparation and evaluation of poly(L-lactic acid) microspheres containing rhEGF for chronic gastric ulcer healing. *J Controlled Release* **75**: 259–269.
- 36 Hedberg EL, Tang A et al. 2002; Controlled release of an osteogenic peptide from injectable biodegradable polymeric composites. *J Controlled Release* **84**: 137–150.
- 37 Henry-Michelland S, Alonso MJ et al. 1987; Attachment of antibiotics to nanoparticles: preparation, drug-release and antimicrobial activity *in vitro*. *Int J Pharmaceut* **35**: 121–127.
- 38 Heritage PL, Loomes LM et al. 1996; Novel polymer-grafted starch microparticles for mucosal delivery of vaccines. *Immunology* **88**(1): 162–168.
- 39 Herrmann J, Bodmeier R. 1995; The effect of particle microstructure on the somatostatin release from poly(lactide) microspheres prepared by a W/O/W solvent evaporation method. *J Controlled Release* **36**(1–2): 63–71.
- 40 Herrmann J, Bodmeier R. 1998; Biodegradable, somatostatin acetate containing microspheres prepared by various aqueous and non-aqueous solvent evaporation methods. *Eur J Pharmaceut Biopharmaceut* **45**: 75–82.
- 41 Holland TA, Tabata Y et al. 2003; *In vitro* release of transforming growth factor- β 1 from gelatin microparticles encapsulated in biodegradable, injectable oligo[poly(ethylene glycol) fumarate] hydrogels. *J Controlled Release* **91**(3): 299–313.
- 42 Hollinger JO, Brekke J et al. 1996; Role of bone substitutes. *Clin Orthop Rel Res* **324**: 55–65.
- 43 Hollinger JO, Leong K. 1996; Poly(α -hydroxy acids): carriers for bone morphogenetic proteins. *Biomaterials* **17**(2): 187–194.
- 44 Hong Y, Gao CY et al. 2005; Collagen-coated polylactide microspheres as chondrocyte microcarriers. *Biomaterials* **26**(32): 6305–6313.
- 45 Hoshino T, Muranishi H et al. 2000; Enhancement of fracture repair in rats with streptozotocin-induced diabetes by a single injection of biodegradable microcapsules containing a bone formation stimulant, TAK-778. *J Biomed Mater Res* **51**: 299–306.
- 46 Hrkach JS, Peracchia MT et al. 1997; Nanotechnology for biomaterials engineering: structural characterization of amphiphilic polymeric nanoparticles by 1H-NMR spectroscopy. *Biomaterials* **18**(1): 27–30.
- 47 Hu Y, Jiang X et al. 2002; Synthesis and characterization of chitosan-poly(acrylic acid) nanoparticles. *Biomaterials* **23**(15): 3193–3201.
- 48 Huang Y-C, Yeh M-K et al. 2003; The characteristics of betamethasone-loaded chitosan microparticles by spray-drying method. *J Microencapsulation* **20**(4): 459–472.
- 49 Huang ZL, Zhao YD et al. 2006; Quantum-dot-tagged microbeads and their use as fluorescent biological probes. *Curr Anal Chem* **2**(1): 59–66.
- 50 Humphrey WR, Erickson LA et al. 1997; The effect of intramural delivery of polymeric nanoparticles loaded with the antiproliferative 2-aminochrome U-86983 on neointimal hyperplasia development in balloon-injured porcine coronary arteries. *Adv Drug Delivery Rev* **24**: 87–108.

AQ6

- 1 Huygh A, Schepers E *et al.* 2002; Microchemical transformation
2 of bioactive glass particles of narrow size range followed for
3 24 months *in vivo*. *J Mater Sci Mater Med* **13**: 315–320.
- 4 Iooss P, Le Ray A-M *et al.* 2001; A new injectable bone substitute
5 combining poly(ϵ -caprolactone) microparticles with biphasic
6 calcium phosphate granules. *Biomaterials* **22**(20): 2785–2794.
- 7 Isobe M, Yamazaki Y *et al.* 1999; The role of recombinant human
8 bone morphogenetic protein-2 in PLGA capsul at an extraskeletal
9 site of the rat. *J Biomed Mater Res* **45**: 36–41.
- 10 Isobe M, Yamazaki Y *et al.* 1996; Bone morphogenetic protein
11 encapsulated with a biodegradable and biocompatible polymer. *J*
12 *Biomed Mater Res* **32**: 433–438.
- 13 Jain RK. 1994; Barriers to drug delivery in solid tumours. *Sci Am* •
14 ●●: 42–49.
- 15 Jalón EG, Blanco-Prieto MJ *et al.* 2003; Increased efficacy of
16 acyclovir-loaded microparticles against Herpes simplex virus type
17 1 in cell culture. *Eur J Pharmaceut Biopharmaceut* **56**: 183–187.
- 18 Janes KA, Calvo P *et al.* 2001a; Polysaccharide colloidal particles as
19 delivery systems for macromolecules. *Adv Drug Delivery Rev* **47**:
20 83–97.
- 21 Janes KA, Fresneau MP *et al.* 2001b; Chitosan nanoparticles as
22 delivery systems for doxorubicin. *J Controlled Release* **73**:
23 255–267.
- 24 Jeong Y, Kang M-K *et al.* 2004; All-trans-retinoic acid
25 release from core-shell type nanoparticles of poly(ϵ -
26 caprolactone)/poly(ethylene glycol) diblock co-polymer. *Int J*
27 *Pharmaceut* **273**: 95–107.
- 28 Jeong Y-L, Cheon J-B *et al.* 1998; Clonazepam release from core-shell
29 type nanoparticles *in vitro*. *J Controlled Release* **51**: 169–178.
- 30 Jiang G, Qiu W *et al.* 2003; Preparation and *in vitro/in vivo* eval-
31 uation of insulin-loaded poly(acryloyl-hydroxyethyl starch)–PLGA
32 composite microspheres. *Pharmaceut Res* **20**(3): 452–459.
- 33 Jiao YY, Ubrich N *et al.* 2002; Preparation and characterization of
34 heparin-loaded polymeric microparticles. *Drug Dev Indust Pharm*
35 **28**(8): 1033–1041.
- 36 Jollivet C, Aubert-Pouessel A *et al.* 2004; Striatal implantation of
37 GDNF releasing biodegradable microspheres promotes recovery
38 of motor function in a partial model of Parkinson's disease.
39 *Biomaterials* **25**: 933–942.
- 40 Jung IL, Phyo KH *et al.* 2005; Spontaneous liberation of intracellular
41 polyhydroxybutyrate granules in *Escherichia coli*. *Res Microbiol*
42 **156**(8): 865–873.
- 43 Kamyshny A, Magdassi S. 2000; Fluorescence immunoassay based
44 on fluorescer microparticles. *Colloids Surfaces B Biointerfaces*
45 **18**(1): 13.
- 46 Katare YK, Muthukumaran T *et al.* 2005; Influence of particle size,
47 antigen load, dose and additional adjuvant on the immune
48 response from antigen loaded PLA microparticles. *Int J Pharmaceut*
49 **301**: 149–160.
- 50 Kato D, Takeuchi M *et al.* 2003; The design of polymer microcarrier
51 surfaces for enhanced cell growth. *Biomaterials* **24**: 4253–4264.
- 52 Kawaguchi H. 2000; Functional polymer microspheres. *Progr Polym*
53 *Sci* **25**: 1171–1210.
- 54 Keegan ME, Whittum-Hudson JA *et al.* 2003; Biomimetic design in
55 microparticulate vaccines. *Biomaterials* **24**: 4435–4443.
- 56 Keshaw H, Forbes A *et al.* 2005; Release of angiogenic growth factors
57 from cells encapsulated in alginate beads with bioactive glass.
58 *Biomaterials* **26**(19): 4171–4179.
- 59 Kidane A, Guimond P *et al.* 2001; The efficacy of oral vaccination
of mice with alginate-encapsulated outer membrane proteins of
Pasteurella haemolytica and One-Shot®. *Vaccine* **19**(17–19): 2637.
- Kim HD, Valentini RF. 1997; Human osteoblast response *in vitro* to
platelet-derived growth factor and transforming growth factor-B
delivered from controlled-release polymer rods. *Biomaterials* **18**:
1175–1184.
- Kim HK, Park TG. 1999; Microencapsulation of human growth
hormone within biodegradable polyester microspheres: protein
aggregation stability and incomplete release mechanism.
Biotechnol Bioeng **65**: 659–667.
- Kim HK, Park TG. 2001; Microencapsulation of dissociable human
growth hormone aggregates within poly(l-lactic-co-glycolic acid)
microparticles for sustained release. *Int J Pharmaceut* **229**(1–2):
107.
- Kim HW, Lee EJ *et al.* 2005; On the feasibility of phosphate glass and
hydroxyapatite engineered coating on titanium. *J Biomed Mater*
Res A **75A**(3): 656–667.
- King TW, Patrick CW Jr. 2000; Development and *in vitro*
characterization of vascular endothelial growth factor (VEGF)-
loaded poly(DL-lactic-co-glycolic acid)/poly(ethylene glycol)
microspheres using a solid encapsulation/single emulsion/solvent
extraction technique. *J Biomed Mater Res* **51**: 383–390.
- Kirker-Head CA. 2000; Potential applications and delivery strategies
for bone morphogenetic proteins. *Adv Drug Delivery Rev* **43**: 65–92.
- Klibanov AL. 2006; Microbubble contrast agents – targeted
ultrasound imaging and ultrasound-assisted drug-delivery
applications. *Invest Radiol* **41**(3): 354–362.
- Knowles JC, Hastings GW. 1993; *In vitro* and *in vivo* investigation of
a range of phosphate glass-reinforced polyhydroxybutyrate-based
degradable composites. *J Mater Sci Mater Med* **4**(2): 102–106.
- Knowles JC, Hastings GW *et al.* 1992; Development of a degradable
composite for orthopedic use – *in vivo* biomechanical and
histological evaluation of two bioactive degradable composites
based on the polyhydroxybutyrate polymer. *Biomaterials* **13**(8):
491–496.
- Ko JA, Park HJ *et al.* 2002; Preparation and characterization of
chitosan microparticles intended for controlled drug delivery. *Int*
J Pharmaceut **249**: 165–174.
- Kobayashi N, Okitsu T *et al.* 2002; Development of a cellulose-
based microcarrier containing cellular adhesive peptides for a
bioartificial liver. *Transpl Proc* **35**: 443–444.
- Kojima K, Ignatz RA *et al.* 2004; Tissue-engineered trachea from
sheep marrow stromal cells with transforming growth factor β 2
released from biodegradable microspheres in a nude rat recipient.
J Thorac Cardiovasc Surg **128**(1): 147–153.
- Komlev VS, Barinov SM *et al.* 2002; A method to fabricate porous
spherical hydroxyapatite granules intended for time-controlled
drug release. *Biomaterials* **23**(16): 3449–3454.
- Koosha F, Muller RH. 1987; Production of polyhydroxybutyrate
(PHB) microparticles and nanoparticles. *Archiv Pharm* **320**(9):
913.
- Koosha F, Muller RH *et al.* 1989; Polyhydroxybutyrate as a drug
carrier. *Crit Rev Therapeut Drug Carrier Syst* **6**(2): 117–130.
- Kreuter J. 1983; Evaluation of nanoparticles as drug-delivery systems
II: comparison of body distribution of nanoparticles with the
body distribution of microspheres (>1 micron), liposomes and
emulsions. *Pharm Acta Helv* **58**: 217–226.
- Kreuter J. 1991; Nanoparticle-based drug delivery systems. *J*
Controlled Release **16**: 169–176.
- Kreuter J, Nefzger N *et al.* 1983; Distribution and elimination
of poly(methyl methacrylate) nanoparticles after subcutaneous
administration to rats. *J Pharmaceut Sci* **72**: 1146–1149.
- Kriwet B, Walter E *et al.* 1998; Synthesis of bioadhesive poly(acrylic
acid) nano- and microparticles using an inverse emulsion
polymerization method for the entrapment of hydrophilic drug
candidates. *J Controlled Release* **56**(1–3): 149.
- Kumar MNVR. 2000; Nano- and microparticles as controlled drug
delivery devices. *J Pharm Pharmaceut Sci* **3**(2): 234–258.
- Kumar N, Langer RS *et al.* 2002; Polyanhydrides: an overview. *Adv*
Drug Delivery Rev **54**: 889–910.
- Labhasetwar V, Bonadio J *et al.* 1999; Gene transfection using
biodegradable nanospheres: results in tissue culture and a rat
osteotomy model. *Colloids Surfaces B Biointerfaces* **16**(1–4):
281–290.
- Lam XM, Duenas ET *et al.* 2000; Sustained release of recombinant
human insulin-like growth factor-I for treatment of diabetes. *J*
Controlled Release **67**(2–3): 281–292.
- Langer R. 1991; Drug delivery systems. *MRS Bull* **XVI**(9): 47–49.
- Le Ray A-M, Chiffolleau S *et al.* 2003; Vancomycin encapsulation
in biodegradable poly(ϵ -caprolactone) microparticles for bone
implantation. Influence of the formulation process on size, drug
loading, *in vitro* release and cytocompatibility. *Biomaterials* **24**(3):
443–449.
- Lee CH, Singla A *et al.* 2001; Biomedical applications of collagen. *Int*
J Pharmaceut **221**(1–2): 1–22.
- Lee JE, Kim KE *et al.* 2004; Effects of controlled release from TGF-
 β 1 from chitosan microspheres on chondrocytes cultured in a
collagen/chitosan/glycosaminoglycan scaffold. *Biomaterials* **25**:
4163–4173.
- Li HY, Chang J. 2004; Fabrication and characterization of bioactive
wollastonite/PHBV composite scaffolds. *Biomaterials* **25**(24):
5473–5480.
- Li HY, Du RL *et al.* 2005; Fabrication, characterization, and *in vitro*
degradation of composite scaffolds based on PHBV and bioactive
glass. *J Biomater Appl* **20**(2): 137–155.
- Li RH, Wozney JM. 2001; Delivering on the promise of bone
morphogenetic proteins. *Trends Biotechnol* **19**(7): 255–265.
- Lim ST, Martin GP *et al.* 2000; Preparation and evaluation of the
in vitro drug release properties and mucoadhesion of novel

- 1 Payne RG, McGonigle JS *et al.* 2002b; Development of an injectable, *in situ* crosslinkable, degradable polymeric carrier for osteogenic cell populations. Part 2. Viability of encapsulated marrow stromal osteoblasts cultured on crosslinking poly(propylene fumarate). *Biomaterials* **23**: 4373–4380.
- 2
- 3 Peracchia MT, Gref R *et al.* 1997; PEG-coated nanospheres from amphiphilic diblock and multiblock co-polymers: investigation of their drug encapsulation and release characteristics. *J Controlled Release* **46**: 223–231.
- 4
- 5 Pereswetoff-Morath L. 1998; Microspheres as nasal drug delivery systems. *Adv Drug Delivery Rev* **29**: 185–194.
- 6
- 7 Perets A, Baruch Y *et al.* 2003; Enhancing the vascularization of three-dimensional porous alginate scaffolds by incorporating controlled release basic fibroblast growth factor microspheres. *J Biomed Mater Res* **65**: 489–497.
- 8
- 9 Perez C, De Jesus P *et al.* 2002; Preservation of lysozyme structure and function upon encapsulation and release from poly(lactic-co-glycolic) acid microspheres prepared by the water-in-oil-in-water method. *Int J Pharmaceut* **248**(1–2): 193–206.
- 10
- 11 Perugini P, Genta I *et al.* 2003; PLGA microspheres for oral osteopenia treatment: preliminary *in vitro/in vivo* evaluation. *Int J Pharmaceut* **256**(1–2): 153–160.
- 12
- 13 Pillai O, Dhanikula AB *et al.* 2001; Drug delivery: an odyssey of 100 years. *Curr Opin Chem Biol* **5**: 439–446.
- 14
- 15 Pillai O, Panchagnula R. 2001; Polymers in drug delivery. *Curr Opin Chem Biol* **5**: 447–451.
- 16
- 17 Piskin E, Tuncel A *et al.* 1993; Monosize microbeads based on polystyrene and their modified forms for some selected medical and biological applications. •••••: 481–501.
- 18
- 19 Pitt CG, Jeffcoat AR *et al.* 1979; Sustained drug delivery systems. I. The permeability of poly(ϵ -caprolactone), poly(DL-lactic acid) and their co-polymers. *J Biomed Mater Res* **13**: 497–507.
- 20
- 21 Podual K, Doyle F *et al.* 2000; Dynamic behaviour of glucose oxidase-containing microparticles of poly(ethylene glycol)-grafted cationic hydrogels in an environment of changing pH. *Biomaterials* **21**(14): 1439.
- 22
- 23 Ponchel G, Irache JM. 1998; Specific and non-specific bioadhesive particulate systems for oral delivery to the gastrointestinal tract. *Adv Drug Delivery Rev* **34**: 191–219.
- 24
- 25 Pérez MH, Zinutti C *et al.* 2000; The preparation and evaluation of poly(ϵ -caprolactone) microparticles containing both a lipophilic and a hydrophilic drug. *J Controlled Release* **65**: 429–438.
- 26
- 27 Qiu Q, Ducheyne P *et al.* 1998; Formation and differentiation of three-dimensional rat marrow stromal cell culture on microcarriers in a rotating-wall vessel. *Tissue Engineering* **4**(1): 19–34.
- 28
- 29 Qiu Q, Ducheyne P *et al.* 1999; Fabrication, characterization and evaluation of bioceramic hollow microspheres used as microcarriers for 3-D bone tissue formation in rotating bioreactors. *Biomaterials* **20**(11): 989–1001.
- 30
- 31 Qiu Q, Ducheyne P *et al.* 2001; 3D Bone tissue engineered with bioactive microspheres in simulated microgravity. *In vitro Cell Dev Biol Anim* **37**(3): 157–165.
- 32
- 33 Rabanel J-M, Hildgen P. 2004; Preparation of hydrogel hollow particles for cell encapsulation by a method of polyester core degradation. *J Microencapsulation* **21**(4): 413–431.
- 34
- 35 Reis RL, Cunha AM. 1995; Characterization of two biodegradable polymers of potential application within the biomaterials field. *J Mater Sci Mater Med* **6**(12): 786–792.
- 36
- 37 Ricci M, Blasi P *et al.* 2005; Ketoprofen controlled release from composite microcapsules for cell encapsulation: effect on post-transplant acute inflammation. *J Controlled Release* **107**(3): 395–407.
- 38
- 39 Rocca JL, Rouchouse A. 1976; Separation of sugars on silica microparticles by high-performance liquid chromatography. *J Chromatogr* **117**(1): 216–221.
- 40
- 41 Rodrigues AP, Hirsch D *et al.* 2005; Production and characterisation of alginate microparticles incorporating *Aeromonas hydrophila* designed for fish oral vaccination. *Process Biochem* (in press).
- 42
- 43 Ronneberger B, Kissel T *et al.* 1997; Biocompatibility of ABA triblock co-polymer microparticles consisting of poly(L-lactic-co-glycolic acid) A-blocks attached to central poly(oxyethylene) B-blocks in rats after intramuscular injection. *Eur J Pharmaceut Biopharmaceut* **43**: 19–28.
- 44
- 45 Rossler B, Kreuter J *et al.* 1994; Effect of collagen microparticles on the stability of retinol and its absorption into hairless mouse skin *in vitro*. *Pharmazie* **49**: 175–179.
- 46
- 47 Rydell N, Sjöholm I. 2004; Oral vaccination against diphtheria using polyacryl starch microparticles as adjuvant. *Vaccine* **22**: 1265–1274.
- 48
- 49 Safarikova M, Roy I *et al.* 2003; Magnetic alginate microparticles for purification of α -amylases. *J Biotechnol* **105**: 255–260.
- 50
- 51 Saito Y, Doi Y. 1994; Microbial synthesis and properties of poly(3-hydroxybutyrate-co-4-hydroxybutyrate) in *Comamonas acidovorans*. *Int J Biol Macromol* **16**(2): 99–104.
- 52
- 53 Salgado AJ, Coutinho OP *et al.* 2005; *In vivo* response to starch-based scaffolds designed for bone tissue engineering applications. *J Biomed Mater Res* (in press).
- 54
- 55 Sanchez A, Tobio M *et al.* 2003; Biodegradable micro- and nanoparticles as long-term delivery vehicles for interferon-alpha. *Eur J Pharmaceut Sci* **18**(3–4): 221–229.
- 56
- 57 Santinho AJP, Pereira NL *et al.* 1999; Influence of formulation on the physicochemical properties of casein microparticles. *Int J Pharmaceut* **186**(2): 191.
- 58
- 59 Santos EM, Radin S *et al.* 1999; Sol-gel derived carrier for the controlled release of proteins. *Biomaterials* **20**(18): 1695–1700.
- 60
- 61 Santos EM, Radin S *et al.* 1998; Si-Ca-P xerogels and bone morphogenetic protein act synergistically on rat stromal marrow cell differentiation *in vitro*. *J Biomed Mater Res* **41**(1): 87–94.
- 62
- 63 Schaffazick SR, Pohlmann AR *et al.* 2003; Freeze-drying polymeric colloidal suspensions: nanocapsules, nanospheres and nanodispersion. A comparative study. *Eur J Pharmaceut Biopharmaceut* **56**: 501–505.
- 64
- 65 Schepers E, Barbier L *et al.* 1998; Implant placement enhanced by bioactive glass particles of narrow size range. *Int J Oral Maxillofac Impl* **13**: 655–665.
- 66
- 67 Schepers E, Declercq M *et al.* 1991; Bioactive glass particulate material as a filler for bone lesions. *Oral Rehabil* **18**: 439–452.
- 68
- 69 Schepers E, Ducheyne P. 1997; Bioactive glass granules of narrow size range for the treatment of oral bony defects: a twenty-four month animal experiment. *J Oral Rehabil* **24**: 171–181.
- 70
- 71 Schepers E, Ducheyne P *et al.* 1993; Bioactive glass particles of limited size range: a new material for the repair of bone defects. *Impl Dent* **2**: 151–156.
- 72
- 73 Schlapp M, Friess W. 2003; Collagen/PLGA microparticle composites for local controlled delivery of gentamicin. *J Pharmaceut Sci* **92**(11): 2145–2151.
- 74
- 75 Seal BL, Otero TC *et al.* 2001; Polymeric biomaterials for tissue and organ regeneration. *Mater Sci Eng* **R34**: 147–230.
- 76
- 77 Sendil D, Gursel I *et al.* 1999; Antibiotic release from biodegradable PHBV microparticles. *J Controlled Release* **59**: 207–217.
- 78
- 79 Shahidi F, Han XQ. 1993; Encapsulation of food ingredients. *Crit Rev Food Sci Nutr* **33**: 501–547.
- 80
- 81 Shi XW, Du YM *et al.* 2005; Ionically crosslinked alginate/carboxymethyl chitin beads for oral delivery of protein drugs. *Macromol Biosci* **5**(9): 881–889.
- 82
- 83 Shinkai M. 2002; Functional magnetic particles for medical application. *J Biosci Bioeng* **94**(6): 606–613.
- 84
- 85 Siepmann J, Faisant N *et al.* 2004; Effect of the size of biodegradable microparticles on drug release: experimental and theory. *J Controlled Release* **96**: 123–134.
- 86
- 87 Silva GA, Costa FJ *et al.* 2004; Synthesis and evaluation of novel bioactive starch/bioactive glass microparticles. *J Biomed Mater Res* **70A**: 442–449.
- 88
- 89 Silva GA, Costa FJ *et al.* 2005; Entrapment ability and release profile of corticosteroids from starch-based particles. *J Biomed Mater Res* **73**: 234–243.
- 90
- 91 Silva GA, Coutinho OP *et al.* 2006; Materials in particulate form for tissue engineering. Part 2. Applications in bone tissue engineering. • *Curr Opin Solid State Mater Sci* (in press).
- 92
- 93 Silvio L, Gurav N *et al.* 1994; Biodegradable microspheres: a new delivery system for growth hormone. *Biomaterials* **15**(11): 931–936.
- 94
- 95 Singh M, Briones M *et al.* 2001a; A novel bioadhesive intranasal delivery system for inactivated influenza vaccines. *J Controlled Release* **70**(3): 267.
- 96
- 97 Singh M, Shirley B *et al.* 2001b; Controlled release of recombinant insulin-like growth factor from a novel formulation of polylactide-co-glycolide microparticles. *J Controlled Release* **70**: 21–28.
- 98
- 99 Sivakumar M, Panduranga Rao K. 2003; Preparation, characterization, and *in vitro* release of gentamicin from coralline hydroxyapatite-alginate composite microspheres. *J Biomed Mater Res* **65**: 222–228.
- 100
- 101 Smidsrød O, Skjåk-Bræk G. 1990; Alginate as immobilization matrix for cells. *Trends Biotechnol* **8**: 71–78.
- 102
- 103 Somavarapu S, Pandit S *et al.* 2005; Effect of Vitamin E TPGS on immune response to nasally delivered diphtheria toxoid loaded poly(caprolactone) microparticles. *Int J Pharmaceut* **298**: 344–347.
- 104

- 1 Song CX, Labhasetwar V et al. 1997; Formulation and
2 characterization of biodegradable nanoparticles for intravascular
3 local drug delivery. *J Controlled Release* **43**(2–3): 197–212.
- 4 Soppimath KS, Aminabhavi TM et al. 2001; Biodegradable polymeric
5 nanoparticle as drug delivery devices. *J Controlled Release*
6 **70**(1–2): 1–20.
- 7 Spegel P, Schweitz L et al. 2001; Molecularly imprinted
8 microparticles for capillary electrochromatography: studies
9 on microparticle synthesis and electrolyte composition.
10 *Electrophoresis* **22**(17): 3833–3841.
- 11 Stenekes RJH, Loebis AE et al. 2001; Degradable dextran
12 microspheres for the controlled release of liposomes. *Int J*
13 *Pharmaceut* **214**(1–2): 17–20.
- 14 Stertman L, Lundgren E et al. 2006; Starch microparticles as a
15 vaccine adjuvant: only uptake in Peyer's patches decides the
16 profile of the immune response. *Vaccine* **24**(17): 3661–3668.
- 17 Streubel A, Siepmann J et al. 2002; Floating microparticles based on
18 low density foam powder. *Int J Pharmaceut* **241**: 279–292.
- 19 Stureson C, Wikingson LD. 2000; Comparison of poly(acryl starch)
20 and poly(lactide-co-glycolide) microspheres as drug delivery
21 system for a rotavirus vaccine. *J Controlled Release* **68**: 441–450.
- 22 Suckow MA, Jarvinen LZ et al. 2002; Immunization of rabbits against
23 a bacterial pathogen with an alginate microparticle vaccine. *J*
24 *Controlled Release* **85**: 227–235.
- 25 Sugiura S, Oda T et al. 2005; Size control of calcium alginate beads
26 containing living cells using micro-nozzle array. *Biomaterials* **26**:
27 3327–3331.
- 28 Swatschek D, Schatton W et al. 2002; Microparticles derived from
29 marine sponge collagen (SCMPs): preparation, characterization
30 and suitability for dermal delivery of all-trans-retinol. *Eur J*
31 *Pharmaceut Biopharmaceut* **54**(2): 125.
- 32 Takada S, Yamagata Y et al. 2003; Sustained release of human
33 growth hormone from microcapsules prepared by a solvent
34 evaporation technique. *J Controlled Release* **88**(2): 229–242.
- 35 Tamilvanan S, Sa B. 2000a; Studies on *in vitro* release behaviour of
36 indomethacin-loaded polystyrene microparticles. *Int J Pharmaceut*
37 **201**(2): 187.
- 38 Tamilvanan S, Sa B. 2000b; Studies on the *in vitro* release
39 characteristics of ibuprofen-loaded polystyrene microparticles. *J*
40 *Microencapsulation* **17**(1): 57–67.
- 41 Tamura T, Fujita F et al. 2002; Anti-tumour effect of intraperitoneal
42 administration of cisplatin-loaded microspheres to human tumour
43 xenografted nude mice. *J Controlled Release* **80**(1–3): 295–307.
- 44 Tao SL, Desai TA. 2003; Microfabricated drug delivery systems: from
45 particles to pores. *Adv Drug Delivery Rev* **55**: 315–328.
- 46 Tatard VM, Venier-Julienne MC et al. 2005; Pharmacologically
47 active microcarriers: a tool for cell therapy. *Biomaterials* **26**:
48 3727–3737.
- 49 Thomson RC, Yaszemski MJ et al. 1998; Hydroxyapatite fibre
50 reinforced poly(α -hydroxy ester) foams for bone regeneration.
51 *Biomaterials* **19**: 1935–1943.
- 52 Tinsley-Brown AM, Fretwell R et al. 2000; Formulation of poly(D,L-
53 lactide-co-glycolic acid) microparticles for rapid plasmid DNA
54 delivery. *J Controlled Release* **66**: 229–241.
- 55 Tiourina O, Sukhorukov GB. 2002; Multilayer alginate-protamine
56 micro-sized capsules: encapsulation of α -chymotrypsin and
57 controlled release study. *Int J Pharmaceut* **242**: 155–161.
- 58 Touvinen L, Peltonen S et al. 2004; Drug release from starch–acetate
59 microparticles and films with and without incorporated α -amylase.
60 *Biomaterials* **25**: 4355–4362.
- 61 Tu J, Bolla S et al. 2005; Alginate microparticles prepared by
62 spray-coagulation method: preparation, drug loading and release
63 characterization. *Int J Pharmaceut* **303**(1–2): 171.
- 64 Tuncel A, Ecevit K et al. 1996; Non-swellable and swellable ethylene
65 glycol dimethacrylate–acrylic acid co-polymer microspheres. *J*
66 *Polym Sci A Polym Chem* **34**: 45–55.
- 67 Ueda H, Tabata Y. 2003; Polyhydroxyalkanoate derivatives in
68 current clinical applications and trials. *Adv Drug Delivery Rev*
69 **55**(4): 501–518.
- 70 van der Lubben IM, Verhoef JC et al. 2001; Chitosan microparticles
71 for oral vaccination: preparation, characterization and preliminary
72 *in vivo* uptake studies in murine Peyer's patches. *Biomaterials*
73 **22**(7): 687.
- 74 Vaz CM, van Doeveren P et al. 2004; Controlled delivery achieved
75 with bi-layer matrix devices produced by co-injection moulding.
76 *Macromol Biosci* **4**(8): 795–801.
- 77 Voigt A, Zintl F. 1999; Hybridoma cell growth and anti-
78 neuroblastoma monoclonal antibody production in spinner flasks
79 using a protein-free medium with microcarriers. *J Biotechnol* **68**:
80 213–226.
- 81 Walter E, Moelling K et al. 1999; Microencapsulation of DNA
82 using poly(lactide-co-glycolide): stability issues and release
83 characteristics. *J Controlled Release* **61**(3): 361.
- 84 Wang J, Chua KM et al. 2004; Stabilization and encapsulation of
85 human immunoglobulin G into biodegradable microspheres. *J*
86 *Colloid Interface Sci* **271**: 92–101.
- 87 Wang X, Ma J et al. 2002; Skeletal repair in rabbits with
88 calcium phosphate cements incorporated phosphorylated chitin.
89 *Biomaterials* **23**(23): 4591–4600.
- 90 Wartlick H, Schmitt BS et al. 2004; Tumour cell delivery of antisense
91 oligonucleotides by human serum albumin nanoparticles. *J*
92 *Controlled Release* **96**: 483–495.
- 93 Wei G, Pettway GJ et al. 2004; The release profiles and bioactivity
94 of parathyroid hormone from poly(lactide-co-glycolic acid)
95 microspheres. *Biomaterials* **25**(2): 345–352.
- 96 Weinhold AR, Besseghir K et al. 1998; Development and evaluation
97 *in vivo* of a long-term delivery system for vapreotide, a
98 somatostatin analogue. *J Controlled Release* **52**: 205–213.
- 99 Weng J, Wang M et al. 2002; Plasma-sprayed calcium phosphate
100 particles with high bioactivity and their use in bioactive scaffolds.
101 *Biomaterials* **23**(13): 2623–2629.
- 102 Whang K, Tsai DC et al. 1998; Ectopic bone formation via rhBMP-2
103 delivery from porous bioabsorbable polymer scaffolds. *J Biomed*
104 *Mater Res* **42**: 491–499.
- 105 Wikingson LD, Sjöholm I. 2002; Polyacryl starch microparticles as
106 adjuvants in oral immunisation, inducing mucosal and systemic
107 immune responses in mice. *Vaccine* **20**: 3355–3363.
- 108 Williams D. 1998; The right time and the right place: the concepts
109 and concerns of drug delivery systems. *Med Device Technol* **9**(2):
110 10–16.
- 111 Winn SR et al. 1998; Sustained release emphasizing recombinant
112 human bone morphogenetic protein 2. *Adv Drug Delivery Rev* **31**:
113 303–318.
- 114 Xu T, Li SL et al. 2003; Preparation and culture of hepatocyte on
115 gelatin microcarriers. *J Biomed Mater Res A* **65A**(2): 306–310.
- 116 Yamazaki Y, Oida S et al. 1996; Ectopic induction of cartilage and
117 bone by bovine bone morphogenetic protein using a biodegradable
118 polymeric reservoir. *J Biomed Mater Res* **30**: 1–4.
- 119 Yan X, Gemeinhart RA. 2005; Cisplatin delivery from poly(acrylic
120 acid-co-methyl methacrylate) microparticles. *J Controlled Release*
121 **106**: 198–208.
- 122 Yang L, Alexandridis P. 2000; Physicochemical aspects of drug
123 delivery and release from polymer-based colloids. *Curr Opin*
124 *Colloid Interface Sci* **5**(1–2): 132.
- 125 Yang Y-Y, Shi M et al. 2003; POE/PLGA composite microspheres:
126 formation and *in vitro* behaviour of double walled microspheres.
127 *J Controlled Release* **88**(2): 201–213.
- 128 Yasugi K, Nagasaki Y et al. 1999; Preparation and characterization
129 of polymer micelles from poly(ethyleneglycol)-poly(D,L-lactide)
130 block co-polymers as potential drug carrier. *J Controlled Release*
131 **62**: 89–100.
- 132 Yenice I, Kas HS et al. 2002; Biodegradable implantable teicoplanin
133 beads for the treatment of bone infections. *Int J Pharmaceut* **242**:
134 271–275.
- 135 Yokomizo AY, Antoniazzi MM et al. 2004; Rabies virus production
136 in high Vero cell density cultures on macroporous microcarriers.
137 *Biotechnol Bioeng* **85**(5): 506–515.
- 138 Youan BC. 2003; Microencapsulation of superoxide dismutase into
139 poly(ϵ -caprolactone) microparticles by reverse micelle solvent
140 evaporation. *Drug Delivery* **10**(4): 283–288.
- 141 Zeller BL, Saleeb FZ et al. 1999; Trends in development of porous
142 carbohydrate food ingredients for use in flavour encapsulation.
143 *Trends Food Sci Technol* **9**: 389–394.
- 144 Zerbo IR, Bronckers ALJJ et al. 2005; Localisation of osteogenic and
145 osteoclastic cells in porous β -tricalcium phosphate particles used
146 for human maxillary sinus floor elevation. *Biomaterials* **26**(12):
147 1445–1451.
- 148 Zhang LG, Pan JL et al. 2003; Studies on the preparation of
149 chitosan microcarriers cross-linked by oxidized lactose and culture
150 of primary hepatocytes. *Artific Cells Blood Substit Immobiliz*
151 *Biotechnol* **31**(3): 293–301.
- 152 Zhang MQ, El Rassi Z. 1999; Capillary electrochromatography with
153 novel stationary phases: II. Studies of the retention behaviour
154 of nucleosides and bases on capillaries packed with octadecyl-
155 sulphonated-silica microparticles. *Electrophoresis* **20**(1): 31–36.
- 156 Zhang Y, Zhuo R. 2005; Synthesis and drug release
157 behaviour of poly(trimethylene carbonate)-poly(ethylene
158 118

TS2

1	glycol)–poly(trimethylene carbonate) nanoparticles. <i>Biomaterials</i>	60
2	26: 2089–2094.	
3	Zhu X, Lu L <i>et al.</i> 2002; Controlled release of NFκB decoy	61
4	oligonucleotides from biodegradable polymer microparticles.	62
5	<i>Biomaterials</i> 23: ●2683–2092.	63
6	Zignani M, Einmahl S <i>et al.</i> 2000; A poly(ortho ester) designed for	64
7	combined ocular delivery of dexamethasone sodium phosphate	65
8		66
9		67
10		68
11		69
12		70
13		71
14		72
15		73
16		74
17		75
18		76
19		77
20		78
21		79
22		80
23		81
24		82
25		83
26		84
27		85
28		86
29		87
30		88
31		89
32		90
33		91
34		92
35		93
36		94
37		95
38		96
39		97
40		98
41		99
42		100
43		101
44		102
45		103
46		104
47		105
48		106
49		107
50		108
51		109
52		110
53		111
54		112
55		113
56		114
57		115
58		116
59		117
		118