

Deposition rate of Ti film prepared by Explorer14 magnetron Sputterer (Graduate Student Fellow Program)

prepared by Swapil Paliwal (4/21/2014)

- Thickness measurement: P7 stylus profiler
- Deposition rate: 17.6 nm/min at 400 W DC

